

KetaSpire® KT-880 GF30

polyetheretherketone

KetaSpire® KT-880 GF30 is the high-flow, 30% glass-fiber reinforced grade of polyetheretherketone (PEEK). This resin offers higher strength and stiffness properties relative to unreinforced KetaSpire® PEEK resin. Reinforcement also affords greater mechanical robustness in structural applications, particularly those with service temperatures approaching 300°C.

KetaSpire® PEEK is produced to the highest industry standards and is characterized by a distinct combination of properties, which include excellent wear resistance,

best-in-class fatigue resistance, ease of melt processing, high purity and excellent chemical resistance to organics, acids and bases.

These properties make it well-suited for applications in healthcare, transportation, electronics, chemical processing and other industrial uses.

- Beige: KT-880 GF30 BG 20
- Black: KT-880 GF30 BK 95

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight	
Features	<ul style="list-style-type: none"> • Autoclave Sterilizable • Biocompatible • Chemical Resistant • E-beam Sterilizable • Ethylene Oxide Sterilizable • Fatigue Resistant • Flame Retardant • Good Dimensional Stability • Good Sterilizability • Heat Sterilizable 	<ul style="list-style-type: none"> • High Flow • High Heat Resistance • High Stiffness • High Strength • Radiation (Gamma) Resistant • Radiation Sterilizable • Radiotranslucent • Steam Resistant • Steam Sterilizable
Uses	<ul style="list-style-type: none"> • Aircraft Applications • Connectors • Dental Applications • Electrical/Electronic Applications • Film • Hospital Goods • Industrial Applications 	<ul style="list-style-type: none"> • Medical Devices • Medical/Healthcare Applications • Oil/Gas Applications • Pump Parts • Seals • Surgical Instruments
Agency Ratings	<ul style="list-style-type: none"> • FAA FAR 25.853a¹ • ISO 10993² 	• MIL P-46183 Type II Class 3
RoHS Compliance	• RoHS Compliant	
Appearance	• Light Beige	
Forms	• Pellets	
Processing Method	<ul style="list-style-type: none"> • Injection Molding • Machining 	• Profile Extrusion

Physical	Dry	Conditioned Unit	Test method
Density / Specific Gravity	1.53	1.53	ASTM D792
Melt Mass-Flow Rate (MFR) (400°C/2.16 kg)	14	14 g/10 min	ASTM D1238

KetaSpire® KT-880 GF30

polyetheretherketone

Physical	Dry	Conditioned	Unit	Test method
Molding Shrinkage ³				ASTM D955
Flow : 3.18 mm	0.10 to 0.30	0.10 to 0.30	%	
Across Flow : 3.18 mm	1.3 to 1.5	1.3 to 1.5	%	
Water Absorption (24 hr)	0.10	0.10	%	ASTM D570
Mechanical	Dry	Conditioned	Unit	Test method
Tensile Modulus				
-- ⁴	10800	10800	MPa	ASTM D638
--	11200	11200	MPa	ISO 527-2/1A/1
Tensile Stress				
Yield	174	174	MPa	ISO 527-2/1A/5
--	162	162	MPa	ASTM D638
Tensile Elongation				
Break ^{4,5}	3.1	3.1	%	ASTM D638
Break	3.1	3.1	%	ISO 527-2/1A/5
Flexural Modulus				
--	10500	10500	MPa	ASTM D790
--	10600	10600	MPa	ISO 178
Flexural Strength				
--	260	260	MPa	ASTM D790
--	239	239	MPa	ISO 178
Compressive Strength	183	183	MPa	ASTM D695
Shear Strength	94.4	94.4	MPa	ASTM D732
Impact	Dry	Conditioned	Unit	Test method
Notched Izod Impact				
--	96	96	J/m	ASTM D256
--	11	11	kJ/m ²	ISO 180
Unnotched Izod Impact				
--	850	850	J/m	ASTM D4812
--	62	62	kJ/m ²	ISO 180
Hardness	Dry	Conditioned	Unit	Test method
Rockwell Hardness (M-Scale)	105	105		ASTM D785
Thermal	Dry	Conditioned	Unit	Test method
Deflection Temperature Under Load				ASTM D648
1.8 MPa, Annealed	315	315	°C	
Glass Transition Temperature	147	147	°C	ASTM D3418
Peak Melting Temperature	343	343	°C	ASTM D3418
CLTE - Flow (-50 to 50°C)	1.9E-5	1.9E-5	cm/cm/°C	ASTM E831
Specific Heat				DSC
50°C	1280	1280	J/kg/°C	
200°C	1700	1700	J/kg/°C	
Thermal Conductivity	0.30	0.30	W/m/K	ASTM E1530

KetaSpire® KT-880 GF30

polyetheretherketone

Electrical	Dry	Conditioned	Unit	Test method
Surface Resistivity	> 1.9E+17	> 1.9E+17	ohms	ASTM D257
Volume Resistivity	3.8E+17	3.8E+17	ohms·cm	ASTM D257
Dielectric Strength (3.00 mm)	16	16	kV/mm	ASTM D149
Dielectric Constant				ASTM D150
60 Hz	3.53	3.53		
1 kHz	3.53	3.53		
1 MHz	3.49	3.49		
Dissipation Factor				ASTM D150
60 Hz	2.0E-3	2.0E-3		
1 kHz	2.0E-3	2.0E-3		
1 MHz	4.0E-3	4.0E-3		
Flammability	Dry	Conditioned	Unit	Test method
Flame Rating				UL 94
0.8 mm	V-0	V-0		
1.6 mm	V-0	V-0		
Fill Analysis	Dry	Conditioned	Unit	Test method
Melt Viscosity (400°C, 1000 sec ⁻¹)	350	350	Pa·s	ASTM D3835

KetaSpire® KT-880 GF30

polyetheretherketone

Injection	Dry Unit
Drying Temperature	150 °C
Drying Time	4.0 hr
Rear Temperature	365 °C
Middle Temperature	371 °C
Front Temperature	377 °C
Nozzle Temperature	382 °C
Mold Temperature	177 to 204 °C
Injection Rate	Fast
Screw Compression Ratio	2.5:1.0 to 3.5:1.0

Notes

Typical properties: these are not to be construed as specifications.

¹ Passes 60s VB flame, smoke and toxicity requirements.

² Only KetaSpire® KT-880 GF30 BG20 is ISO 10993 certified

³ 5" x 0.5" x 0.125"

⁴ 5.0 mm/min

⁵ Crystallized



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.