

# KetaSpire® KT-880

## polyetheretherketone

KetaSpire® KT-880 is a high flow grade of unreinforced polyetheretherketone (PEEK) supplied in pellet form. KetaSpire® PEEK is produced to the highest industry standards and is characterized by a distinct combination of properties, which include excellent wear resistance, best-in-class fatigue resistance, ease of melt processing, high purity and excellent chemical resistance to organics, acids and bases.

These properties make it well-suited for applications in healthcare, transportation, electronics, chemical processing and other industrial uses. KetaSpire® KT-880 NT can be easily processed using typical injection molding processes.

This resin is also available as KT-880P in a natural-color coarse powder form for compounding.

Pellets of KT-880 are supplied lightly dusted with the lubricant calcium stearate (0.01% level) to aid with pellet conveyance in plastication screws. The equivalent unlubricated natural color grade of high flow KetaSpire® is available as KT-880 NL.

- Black: KT-880 BK 95
- Natural: KT-880 NT

### General

Material Status	• Commercial: Active	
Availability	<ul style="list-style-type: none"> <li>• Africa &amp; Middle East</li> <li>• Asia Pacific</li> <li>• Europe</li> </ul>	<ul style="list-style-type: none"> <li>• Latin America</li> <li>• North America</li> </ul>
Features	<ul style="list-style-type: none"> <li>• Autoclave Sterilizable</li> <li>• Biocompatible</li> <li>• Chemical Resistant</li> <li>• Ductile</li> <li>• E-beam Sterilizable</li> <li>• Ethylene Oxide Sterilizable</li> <li>• Fatigue Resistant</li> <li>• Flame Retardant</li> <li>• Good Dimensional Stability</li> <li>• Good Impact Resistance</li> </ul>	<ul style="list-style-type: none"> <li>• Good Sterilizability</li> <li>• Heat Sterilizable</li> <li>• High Flow</li> <li>• High Heat Resistance</li> <li>• Radiation (Gamma) Resistant</li> <li>• Radiation Sterilizable</li> <li>• Radiotranslucent</li> <li>• Steam Resistant</li> <li>• Steam Sterilizable</li> </ul>
Uses	<ul style="list-style-type: none"> <li>• Aircraft Applications</li> <li>• Connectors</li> <li>• Dental Applications</li> <li>• Electrical/Electronic Applications</li> <li>• Film</li> <li>• Hospital Goods</li> <li>• Industrial Applications</li> </ul>	<ul style="list-style-type: none"> <li>• Medical Devices</li> <li>• Medical/Healthcare Applications</li> <li>• Oil/Gas Applications</li> <li>• Pump Parts</li> <li>• Seals</li> <li>• Surgical Instruments</li> </ul>
Agency Ratings	<ul style="list-style-type: none"> <li>• ISO 10993</li> <li>• MIL P-46183 Type I</li> </ul>	<ul style="list-style-type: none"> <li>• NSF STD-51<sup>1</sup></li> <li>• USP Class VI<sup>2</sup></li> </ul>
RoHS Compliance	• RoHS Compliant	
Appearance	• Black	• Natural Color
Forms	• Pellets <sup>3</sup>	
Processing Method	<ul style="list-style-type: none"> <li>• Extrusion Blow Molding</li> <li>• Fiber (Spinning) Extrusion</li> <li>• Film Extrusion</li> <li>• Injection Molding</li> </ul>	<ul style="list-style-type: none"> <li>• Machining</li> <li>• Profile Extrusion</li> <li>• Thermoforming</li> <li>• Wire &amp; Cable Extrusion</li> </ul>

# KetaSpire® KT-880

## polyetheretherketone

Physical	Typical Value	Unit	Test method
Density / Specific Gravity	1.30		ASTM D792
Melt Mass-Flow Rate (MFR) (400°C/2.16 kg)	36	g/10 min	ASTM D1238
Molding Shrinkage <sup>4</sup>			ASTM D955
Flow	1.4 to 1.6	%	
Across Flow	1.5 to 1.7	%	
Water Absorption (24 hr)	0.10	%	ASTM D570
Mechanical	Typical Value	Unit	Test method
Tensile Modulus			
-- <sup>5</sup>	3700	MPa	ASTM D638
--	4000	MPa	ISO 527-2/1A/1
Tensile Stress			
Yield	102	MPa	ISO 527-2/1A/50
-- <sup>6</sup>	100	MPa	ASTM D638
Tensile Elongation			
Yield <sup>7</sup>	5.2	%	ASTM D638
Yield	5.0	%	ISO 527-2/1A/50
Break <sup>7</sup>	10 to 20	%	ASTM D638
Break	10 to 20	%	ISO 527-2/1A/50
Flexural Modulus			
--	3800	MPa	ASTM D790
--	3900	MPa	ISO 178
Flexural Strength			
--	153	MPa	ASTM D790
--	134	MPa	ISO 178
Compressive Strength	123	MPa	ASTM D695
Shear Strength	95.1	MPa	ASTM D732
Poisson's Ratio	0.37		ASTM E132
Impact	Typical Value	Unit	Test method
Notched Izod Impact			
--	53	J/m	ASTM D256
--	4.9	kJ/m <sup>2</sup>	ISO 180
Unnotched Izod Impact	No Break		ASTM D4812 ISO 180
Hardness	Typical Value	Unit	Test method
Rockwell Hardness (M-Scale)	102		ASTM D785
Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Annealed	160	°C	
Glass Transition Temperature	147	°C	ASTM D3418
Peak Melting Temperature	343	°C	ASTM D3418
CLTE - Flow (-50 to 50°C)	5.0E-5	cm/cm/°C	ASTM E831
Specific Heat			DSC
50°C	1330	J/kg/°C	
200°C	1930	J/kg/°C	

# KetaSpire® KT-880

polyetheretherketone

Thermal	Typical Value	Unit	Test method
Thermal Conductivity	0.25	W/m/K	ASTM E1530

Electrical	Typical Value	Unit	Test method
Surface Resistivity	> 1.9E+17	ohms	ASTM D257
Volume Resistivity	3.8E+17	ohms·cm	ASTM D257
Dielectric Strength (3.00 mm)	15	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
60 Hz	3.10		
1 kHz	3.01		
1 MHz	3.07		
Dissipation Factor			ASTM D150
60 Hz	1.0E-3		
1 kHz	1.0E-3		
1 MHz	3.0E-3		

Flammability	Typical Value	Unit	Test method
Flame Rating (> 3.0 mm, Natural)	V-0		UL 94

Fill Analysis	Typical Value	Unit	Test method
Melt Viscosity (400°C, 1000 sec <sup>-1</sup> )	150	Pa·s	ASTM D3835


# KetaSpire® KT-880

polyetheretherketone


---

Injection	Typical Value	Unit
Drying Temperature	150	°C
Drying Time	4.0	hr
Rear Temperature	355	°C
Middle Temperature	365	°C
Front Temperature	370	°C
Nozzle Temperature	375	°C
Mold Temperature	175 to 205	°C
Injection Rate	Fast	
Screw Compression Ratio	2.5:1.0 to 3.5:1.0	

Isothermal Stress vs. Strain (ISO 11403-1)



Viscosity vs. Shear Rate (ISO 11403-2)



# KetaSpire® KT-880

polyetheretherketone

---

## Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Only KT-880 NT has been NSF STD-51 certified.

<sup>2</sup> KT-880 NT only

<sup>3</sup> Pellets are supplied lightly dusted with the lubricant calcium stearate (0.01% level). For non-lubricated, natural color grade, order KT-880 NL.

<sup>4</sup> 5" x 0.5" x 0.125" (127 x 12.7 x 3.18mm)

<sup>5</sup> 1.0 mm/min

<sup>6</sup> 51 mm/min

<sup>7</sup> 50 mm/min



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.