

PES 3200P

Property	ASTM	Typical Values			
	Test	U.S. Customary Units		SI Units	
	Method	Value	Units	Value	Units
General					
Specific Gravity	D 792	1.37		1.37	
Moisture Content ⁽²⁾	P/QA/I/043	0.5	%	0.5	%
Volatile Content	P/QA/I/306	0.5	%	0.5	%
Intrinsic viscosity in DMF@25°C	D 2857	0.23	dl/g	0.23	dl/g
Color of 10% wt/wt solution in DMF	APHA	100		100	
Molecular weight (Mw) by GPC ⁽³⁾	P/QA/I/314	125000		125000	
Viscosity of 25%(w/w) solution in NMP @25°C	P/QA/I/326	2300	cps	2300	cps
Mechanical ⁽¹⁾					
Tensile Strength	D 638	13.0	kpsi	90	MPa
Tensile Modulus	D 638	363	kpsi	2500	MPa
Tensile Elongation at Break	D 638	25-75	%	25-75	%
Flexural Strength	D 790	16.7	kpsi	115	MPa
Flexural Modulus	D 790	363	kpsi	2500	MPa
Impact Strength- Notched Izod	D 256	1.0	ft-lb/in	55	J/m

⁽¹⁾ These properties has been determined from injection molded test specimen under ideal processing parameters and conditioned at 23+/- 2°C and 50%RH .

⁽²⁾ Moisture is measured at the time of packing. GAFONE PES is hygroscopic and may absorb moisture during storage and therefore should be dried at 150°C for a minimum of 3 hours before use.

⁽³⁾ Molecular weight determination is done using polystyrene as reference standard.

Product Safety and Emergency Service

For product safety information or a Material Safety Data Sheet on a product of Solvay Advanced Polymers

1 (800) 621-4557

1 (770) 772-8880 outside of U.S.

For information or help in an emergency such as a spill, leak, fire or explosion, call day or night:

Emergency Health Information

1 (800) 621-4590

1 (770) 772-5177 outside of U.S.

Emergency Spill Information

CHEMTREC 1 (800) 424-9300

1 (703) 527-3887 outside of U.S.

collect calls accepted

For Additional Information

Technical Service

1 (800) 621-4557

Customer Service

1 (800) 848-9744

GAFONE is a trademark of Solvay Advanced Polymers, L.L.C.

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Advanced Polymers, L.L.C. nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. Solvay Advanced Polymers, L.L.C. reserves the right to make additions, deletions, or modifications to the information at any time without prior notification.