

AG-341

RADEL AG-341 resin is a 20% glass fiber reinforced polyethersulfone-based blend. This product offers high rigidity, tensile strength, creep resistance, dimensional stability, and chemical resistance, while maintaining most of the other basic characteristics of polyethersulfone. The combination of structural properties and cost effectiveness

of this resin makes it an attractive alternative to metal in many engineering applications.

RADEL AG-341 resin can be fabricated with conventional injection molding equipment. It is an opaque, beige or tan material in its natural form and it may be readily colored.

Typical Properties of RADEL AG-341 Resin

Property	ASTM Test Method	Typical Values ⁽¹⁾			
		U.S. Customary Units		SI Units	
		Value	Units	Value	Units
Mechanical					
Tensile Strength	D 638	17.3	kpsi	119	MPa
Tensile Elongation	D 638	3.1	%	3.1	%
Tensile Modulus	D 638	980	kpsi	6.76	GPa
Flexural Strength	D 790	24.5	kpsi	169	MPa
Flexural Modulus	D 790	860	kpsi	5.93	GPa
Notched Izod	D 256	1.2	ft-lb/in	64	J/m
Thermal					
Deflection Temperature ⁽²⁾ at 264 psi (1.8 MPa)	D 648	405	°F	207	°C
General					
Specific Gravity	D 1505	1.45		1.45	
Water Absorption, 24 hours	D 570	0.45	%	0.45	%
Melt Flow at 380°C (716°F), 2.16 kg	D 1238	18	g/10 min	18	g/10 min
Mold Shrinkage	D 955	0.4	%	0.4	%

⁽¹⁾ Properties of individual batches will vary within specification limits. Properties are typical of uncolored material. Colorants or other additives may alter properties.

⁽²⁾ As molded, not annealed, 0.125 in. (3.2 mm) bar thickness.

Drying

RADEL AG-341 resin must be dried completely prior to melt processing. Incomplete drying will result in defects in the formed part ranging from surface streaks to severe bubbling. Because the polymer blend is thermally and hydrolytically stable, molding wet resin does not usually result in degradation; therefore, the defective parts can usually be recovered as regrind.

Pellets of RADEL AG-341 resin can be dried on trays in a circulating air oven or in a hopper dryer. Recommended drying conditions are: 2.5 hours at 350°F (177°C); or 3.5 hours at 300°F (149°C); or 4.5 hours at 275°F (135°C). Note: Do not dry below 275°F (135°C). Dried resin should be handled carefully to prevent reabsorption of moisture from the atmosphere by employing dry containers and covered hoppers.

Injection Molding

RADEL AG-341 resin can be readily injection molded in most screw injection machines. Stock temperature requirements will generally range from 650° to 750°F (343° to 399°C), depending on mold design and the type of equipment being used. A general purpose, 2:1 compression ratio screw is recommended, with back pressures of 50 to 100 psi (0.3 to 0.7 MPa). Injection speeds should be as fast as possible, consistent with part appearance requirements. Mold temperatures of at least 280°F (138°C) are suggested. In the case of long-flow or thin-walled parts, or where low residual stresses are required, mold temperatures as high as 300° to 325°F (149° to 163°C) can be used.

Standard Packaging and Labeling

RADEL AG-341 resin is packaged in multiwall paper bags containing 55.115 pounds (25 kg) of material. Special packaging can be supplied upon request. Individual packages will be plainly marked with the product number, the color, the lot number, and the net weight.

Precautionary Labeling

On the basis of the toxicological, physical, and chemical properties of RADEL AG-341 resin, labeling used on containers is as follows:

Caution! Handling and/or processing this material may generate a dust which can cause mechanical irritation of the eyes, skin, nose, and throat.

Product Safety and Emergency Service

For product safety information or a Material Safety Data Sheet on a product of Solvay Advanced Polymers

1 (800) 621-4557

1 (770) 772-8880 outside of U.S.

For information or help in an emergency such as a spill, leak, fire or explosion, call day or night:

Emergency Health Information

1 (800) 621-4590

1 (770) 772-5177 outside of U.S.

Emergency Spill Information

CHEMTREC 1 (800) 424-9300

1 (703) 527-3887 outside of U.S.

collect calls accepted

For Additional Information

Technical Service

1 (800) 621-4557

Customer Service

1 (800) 848-9744

RADEL is a registered trademark of Solvay Advanced Polymers, L.L.C.

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Advanced Polymers, L.L.C. nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. Solvay Advanced Polymers, L.L.C. reserves the right to make additions, deletions, or modifications to the information at any time without prior notification.