

Veradel® 3600

polyethersulfone

Veradel® 3600 polyethersulfone (PESU) is a very high melt flow, transparent grade that offers high heat deflection temperatures, excellent toughness and dimensional stability, and resistance to steam, boiling water and mineral acids. Other desirable properties include thermal stability, creep resistance and inherent flame resistance.

Three other grades are available: Veradel® 3200, a low melt flow grade that can be processed by extrusion or injection molding and Veradel® 3300, a medium melt flow grade suggested for general purpose injection molding and Veradel® 3400, a high melt flow grade designed for easy molding of parts with thin walls or long flow lengths.

Veradel® 3600 is suggested for compounding, especially of glass or carbon fiber reinforced compounds. It is FDA compliant and is therefore approved for direct food contact.

Veradel® PESU was formerly marketed as Gafone™ PESU.

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Features	• Acid Resistant • Chemical Resistant • Creep Resistant • Flame Retardant • Good Adhesion • Good Dimensional Stability • Good Thermal Stability	• Good Toughness • High Flow • High Heat Resistance • High Tensile Strength • Hydrolysis Resistant • Low Molecular Weight • Medium Rigidity
Uses	• Compounding	
RoHS Compliance	• RoHS Compliant	
Appearance	• Transparent - Slight Yellow	
Forms	• Pellets	
Processing Method	• Compounding	• Injection Molding

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	--	1.37	ASTM D792
	--	1.37 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (380°C/2.16 kg)	75	g/10 min	ASTM D1238 ISO 1133
Molding Shrinkage - Flow	0.60	%	ASTM D955
Water Absorption ¹ (24 hr)	0.50	%	ASTM D570
Water Absorption - 30 days ¹	1.9	%	ASTM D570

Mechanical

	Typical Value	Unit	Test method
Tensile Modulus	--	2690 MPa	ASTM D638
	--	2700 MPa	ISO 527-2

Veradel® 3600

polyethersulfone

Mechanical	Typical Value	Unit	Test method
Tensile Strength			
--	88.9	MPa	ASTM D638
--	90.0	MPa	ISO 527-2
Tensile Elongation			
Yield	6.5	%	ASTM D638
Yield	6.6	%	ISO 527-2
Break	30	%	ISO 527-2
Flexural Modulus			
--	2620	MPa	ASTM D790
--	2750	MPa	ISO 178
Flexural Strength			
--	125	MPa	ASTM D790
--	130	MPa	ISO 178
Impact	Typical Value	Unit	Test method
Charpy Notched Impact Strength	6.0	kJ/m ²	ISO 179
Notched Izod Impact			
--	53	J/m	ASTM D256
--	5.6	kJ/m ²	ISO 180
Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, Injection Molded	200	°C	ASTM D648
1.8 MPa, Unannealed	203	°C	ISO 75-2/A
CLTE - Flow	5.2E-5	cm/cm/°C	ASTM D696 ISO 11359-2
RTI Elec (3.0 mm)	180	°C	UL 746
RTI Imp (3.0 mm)	180	°C	UL 746
RTI Str (3.0 mm)	190	°C	UL 746
Electrical	Typical Value	Unit	Test method
Volume Resistivity			
--	1.7E+15	ohms·cm	ASTM D257
--	1.7E+13	ohms·m	IEC 62631-3-1
Dielectric Strength			
0.800 mm	31	kV/mm	ASTM D149 IEC 60243-1
3.00 mm	15	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
60 Hz	3.51		
1 kHz	3.50		
1 MHz	3.54		
Dissipation Factor			ASTM D150
60 Hz	1.7E-3		
1 kHz	2.2E-3		
1 MHz	5.6E-3		
Comparative Tracking Index	125	V	IEC 60112

Veradel[®] 3600

polyethersulfone

Flammability	Typical Value	Unit	Test method
Flame Rating ² (1.5 mm)	V-0		UL 94

Injection	Typical Value	Unit
Drying Temperature	177	°C
Drying Time	2.5	hr
Processing (Melt) Temp	343 to 385	°C
Mold Temperature	149 to 163	°C
Injection Rate	Fast	
Screw Compression Ratio	2.2:1.0	

Extrusion	Typical Value	Unit
Drying Temperature	177	°C
Drying Time	2.5	hr
Cylinder Zone 1 Temp.	335 to 391	°C
Cylinder Zone 2 Temp.	335 to 391	°C
Cylinder Zone 3 Temp.	335 to 391	°C
Cylinder Zone 4 Temp.	335 to 391	°C
Cylinder Zone 5 Temp.	335 to 391	°C
Adapter Temperature	327 to 371	°C
Melt Temperature	343 to 391	°C
Die Temperature	327 to 371	°C

Notes

Typical properties: these are not to be construed as specifications.

¹ 3.2 mm thick 50 mm dia disk

² These flammability ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva[®] family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.