

# Veradel® 3600RP

## polyethersulfone

Veradel® 3600RP hydroxyl-functionalized polyethersulfone (r-PESU) is an amorphous, high-temperature sulfone polymer featuring reactive end groups to enhance solubility for dissolving or dispersing into solutions and to improve adhesion to substrates when used as a coating.

Veradel® 3600RP r-PESU offers excellent toughness and outstanding hydrolytic resistance. It resists attack from steam, boiling water and mineral acids. Cast films or coatings of r-PESU are transparent and have additional desirable properties, including long term thermal stability, excellent metal adhesion and formability and inherent flame resistance.

Veradel® r-PESU polymers are available in two molecular weight regimes. Veradel® 3000RP is a high molecular

weight sulfone polymer with a relatively low level of functionality while Veradel® 3600RP has a lower molecular weight sulfone polymer (approximately half the molecular weight of the Veradel® 3000RP) with roughly 3-5 times higher level of functionality. The differences in molecular weight results in highly varied levels of viscosity, when measured under similar conditions.

Typical applications include high-temperature coating formulations and specialty adhesives.

All Veradel® r-PESU polymers are produced at Solvay's state-of-the-art, world-scale facility in Panoli, India under ISO 9001:2000 and ISO 14001:2004 certified quality management systems.

### General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Features	• Acid Resistant • Chemical Resistant • Creep Resistant • Flame Retardant • Good Adhesion • Good Dimensional Stability • Good Thermal Stability	• Good Toughness • High Flow • High Heat Resistance • High Tensile Strength • Hydrolysis Resistant • Low Molecular Weight • Medium Rigidity
Uses	• Adhesives • Binder	• Coating Applications
Agency Ratings	• NSF STD-51 <sup>1</sup>	
RoHS Compliance	• Contact Manufacturer	
Appearance	• Transparent - Slight Yellow	
Forms	• Granules	• Powder
Processing Method	• Coating • Solution Processing	• Spraying

### Physical

	Typical Value	Unit	Test method
Solution Viscosity			Internal Method
-- <sup>2</sup>	80	mPa·s	
-- <sup>3</sup>	560	mPa·s	
Moisture Content - Measured at time of packing	1.5	%	Internal Method
OH End Groups - Titration	170	µeq/g	Internal Method
Particle Size - D50 Sieve measurement	250	µm	Internal Method
Residual Solvent - Gas Chromatography	1.5	%	Internal Method

# Veradel® 3600RP

polyethersulfone

Mechanical	Typical Value	Unit	Test method
Tensile Modulus	2700	MPa	ASTM D638
Tensile Strength	90.0	MPa	ASTM D638
Tensile Elongation (Yield)	6.5	%	ASTM D638
Flexural Modulus	2600	MPa	ASTM D790
Flexural Strength	2.60	MPa	ASTM D790

  

Impact	Typical Value	Unit	Test method
Notched Izod Impact	53	J/m	ASTM D256

  

Thermal	Typical Value	Unit	Test method
Glass Transition Temperature	220	°C	DSC

## Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Maximum Temperature of Use: 124°C (356°F)

<sup>2</sup> 25% solution in DMAc at 40°C (measured at 35% solids)

<sup>3</sup> 35% solution in DMAc at 40°C (measured at 35% solids)



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.