

# Hyflon® PFA P450

## perfluoroalkoxy

Hyflon® PFA is a unique family of semi-crystalline, melt processable perfluoropolymers which combine excellent mechanical characteristics to unique properties such as chemical inertness, heat resistance, inherent flame resistance, low surface energy, and exceptional dielectric properties. Hyflon® PFA resins have been designed to retain their properties over a wide range of temperatures from cryogenic to 250-260°C (482-500°F) and are the material of choice in applications such as linings in the Chemical

Process Industry, specialty cables, semiconductor industry, aerospace, and other challenging industries.

Hyflon® PFA P450 is a medium molecular weight, high melt flow rate multi purpose resin designed for cable extrusion and injection molding. Hyflon® PFA P450 has obtained UL758 recognition for continuous use at 260°C (500°F) and is an ASTM D3307 - Type I resin.

### General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Features	• Flame Retardant • High Flow • High Heat Resistance	• Medium Molecular Weight • Semi Crystalline
Uses	• Aerospace Applications • Cable Jacketing	• Liners • Semiconductor Molding Compounds
Agency Ratings	• ASTM D3307 Type I	• UL 758
Forms	• Pellets	
Processing Method	• Extrusion	• Injection Molding

### Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	2.13 to 2.18		ASTM D792
Melt Mass-Flow Rate (MFR) (372°C/5.0 kg)	10 to 17	g/10 min	ASTM D1238

### Mechanical

	Typical Value	Unit	Test method
Tensile Modulus <sup>1</sup> (23°C)	500 to 600	MPa	ASTM D1708
Tensile Strength (Break, 23°C)	> 21.0	MPa	ASTM D1708
Tensile Elongation (Break, 23°C)	> 280	%	ASTM D1708
Flex Life (300.0 µm)	4.0E+3 to 6.0E+3	Cycles	ASTM D2176

### Impact

	Typical Value	Unit	Test method
Charpy Notched Impact Strength	No Break		ASTM D256

### Hardness

	Typical Value	Unit	Test method
Durometer Hardness (Shore D)	55 to 60		ASTM D2240

### Thermal

	Typical Value	Unit	Test method
Continuous Use Temperature	260	°C	
Melting Temperature	300 to 310	°C	ASTM D3307
Peak Crystallization Temperature (DSC)	275 to 285	°C	DSC
CLTE - Flow	1.2E-4 to 2.0E-4	cm/cm/°C	ASTM D696
Specific Heat (23°C)	900 to 1100	J/kg/°C	DSC

# Hyflon® PFA P450

perfluoroalkoxy

Thermal	Typical Value	Unit	Test method
Thermal Conductivity (40°C)	0.20	W/m/K	ASTM C177
Crystallization Heat	25.0 to 35.0	J/g	DSC
Heat of Fusion	25.0 to 35.0	J/g	DSC

Electrical	Typical Value	Unit	Test method
Surface Resistivity	> 1.0E+17	ohms	ASTM D257
Volume Resistivity	> 1.0E+17	ohms·cm	ASTM D257
Dielectric Strength	35 to 40	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
23°C, 50 Hz	2.10		
23°C, 100 kHz	2.10		
Dissipation Factor			ASTM D150
23°C, 50 Hz	< 5.0E-4		
23°C, 100 kHz	< 5.0E-4		

Flammability	Typical Value	Unit	Test method
Flame Rating	V-0		UL 94
Oxygen Index	95	%	ASTM D2863

## Additional Information

### PROCESSING

- Because PFA is corrosive in the melt, machinery used to process Hyflon should be lined with corrosion resistant alloys. Clean, reworked material can be used up to 25% in weight.

### HEALTH SAFETY AND ENVIRONMENT

- Hyflon PFA P450 is a very inert polymer and it is not harmful if used and handled according to standard processing procedures. If handled inappropriately, it may release harmful toxic chemicals. Please refer to the Material Safety Data Sheets for more information on handling and safety.

### PACKAGING AND STORAGE

- Hyflon PFA P450 resin is available in 25 kg (55 lbs) and 500 kg (1102 lbs) packaging. Though it has an indefinite shelf life, it is recommended to store it in a clean area, protected by direct sun light and possible contamination.

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> 1.0 mm/min



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.