

Amodel® A-1145 HS LZT

polyphthalamide

Amodel® A-1145 HS LZT is an NIR laser transmissive, 45% glass reinforced, heat stabilized polyphthalamide (PPA) with a high heat deflection temperature, very high flexural modulus and very high tensile strength. Excellent creep resistance and low moisture absorption are also

characteristic of this resin. This grade is designed to be paired with other Amodel® black grades for black-on-black laser welding applications.

- Black: Amodel® A-1145 HS LZT BK 979

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Glass Fiber, 45% Filler by Weight	
Additive	• Heat Stabilizer	
Features	• Chemical Resistant • Creep Resistant • Good Dimensional Stability • Good Stiffness	• High Heat Resistance • High Strength • High Temperature Strength • Low Moisture Absorption
Uses	• Automotive Applications • Automotive Electronics • Automotive Under the Hood • Connectors • Housings • Industrial Applications	• Industrial Parts • Machine/Mechanical Parts • Metal Replacement • Power/Other Tools • Valves/Valve Parts
RoHS Compliance	• RoHS Compliant	
Appearance	• Black	
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Typical Value	Unit	Test method
Density	1.59	g/cm ³	ISO 1183/A
Molding Shrinkage			ASTM D955
Flow	0.20	%	
Across Flow	0.60	%	
Water Absorption (24 hr)	0.12	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tensile Modulus			
--	17200	MPa	ASTM D638
23°C	16800	MPa	ISO 527-2
Tensile Stress			
Break, 23°C	263	MPa	ISO 527-2
--	259	MPa	ASTM D638
Tensile Elongation			
Break	2.6	%	ASTM D638
Break, 23°C	2.7	%	ISO 527-2

Amodel® A-1145 HS LZT

polyphthalamide

Mechanical	Typical Value	Unit	Test method
Flexural Modulus			
--	13800	MPa	ASTM D790
23°C	15900	MPa	ISO 178
Flexural Strength			
--	363	MPa	ASTM D790
23°C	377	MPa	ISO 178
Impact	Typical Value	Unit	Test method
Charpy Notched Impact Strength (23°C)	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	92	kJ/m ²	ISO 179/1eU
Notched Izod Impact			
--	110	J/m	ASTM D256
23°C	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
--	1100	J/m	ASTM D256
23°C	61	kJ/m ²	ISO 180/1U
Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			
0.45 MPa, Annealed, 3.20 mm	301	°C	ASTM D648
1.8 MPa, Unannealed	281	°C	ISO 75-2/A
1.8 MPa, Annealed, 3.20 mm	287	°C	ASTM D648
Peak Melting Temperature	310	°C	ASTM D3418
Optical	Typical Value	Unit	Test method
Transmittance (2000 µm, 940 nm)	38.0	%	ASTM D1003

Amodel® A-1145 HS LZT

polyphthalamide

Injection	Typical Value	Unit
Drying Temperature	120	°C
Drying Time	4.5	hr
Suggested Max Moisture	0.045	%
Rear Temperature	304 to 318	°C
Front Temperature	316 to 329	°C
Processing (Melt) Temp	321 to 343	°C
Mold Temperature	135	°C

Injection Notes

Storage:

- Amodel® compounds are shipped in moisture-resistant packages at moisture levels according to specifications. Sealed, undamaged bags should be preferably stored in a dry room at a maximum temperature of 50°C (122°F) and should be protected from possible damage. If only a portion of a package is used, the remaining material should be transferred into a sealable container. It is recommended that Amodel® resins be dried prior to molding following the recommendations found in this datasheet and/or in the Amodel® processing guide.

Notes

Typical properties: these are not to be construed as specifications.



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.