

Ryton® QA200N

polyphenylene sulfide

Ryton® QA200N (granular powder) unfilled polyphenylene sulfide exhibits excellent thermal stability and chemical resistance.

General

Material Status	• Commercial: Active
Availability	<ul style="list-style-type: none"> • Asia Pacific • Europe • Latin America • North America
Features	<ul style="list-style-type: none"> • Chemical Resistant • Good Thermal Stability
Uses	• Compounding
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Forms	• Powder
Processing Method	• Injection Molding

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.34		ASTM D792
Melt Mass-Flow Rate (MFR) ¹ (316°C/5.0 kg)	100	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	1.0	%	
Water Absorption (24 hr, 23°C)	0.050	%	ASTM D570
Ash Content	0.1	wt%	ISO 3451-1
Volatiles (150°C)	< 0.3	wt%	

Mechanical

	Typical Value	Unit	Test method
Tensile Modulus	3400	MPa	ISO 527-2
Tensile Stress	80.0	MPa	ISO 527-2
Tensile Strain (Break)	4.0	%	ISO 527-2
Flexural Modulus	3400	MPa	ISO 178
Flexural Stress	140	MPa	ISO 178

Impact

	Typical Value	Unit	Test method
Notched Izod Impact			
3.18 mm	53	J/m	ASTM D256
--	4.0	kJ/m ²	ISO 180/A

Thermal

	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	160	°C	
1.8 MPa, Unannealed	95.0	°C	
Glass Transition Temperature	90.0	°C	ISO 11357-2
Vicat Softening Temperature	> 180	°C	ISO 306
Melting Temperature	280	°C	ISO 11357-3

Ryton® QA200N

polyphenylene sulfide

Thermal	Typical Value	Unit	Test method
CLTE - Flow			ASTM E831
-50 to 50°C	5.0E-5	cm/cm/°C	
100 to 200°C	1.2E-4	cm/cm/°C	
Thermal Conductivity	0.29	W/m/K	

Electrical	Typical Value	Unit	Test method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	24	kV/mm	ASTM D149
Dielectric Constant (25°C, 1 MHz)	3.20		ASTM D150
Dissipation Factor (25°C, 1 MHz)	2.0E-3		ASTM D150

Flammability	Typical Value	Unit	Test method
Flame Rating (1.6 mm, Tested by CP Chemical)	V-0		UL 94
Oxygen Index	44	%	ASTM D2863

Notes

Typical properties: these are not to be construed as specifications.

¹ Procedure B



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.