

Ryton® QC160P

polyphenylene sulfide

Ryton® QC160P (pelletized) polyphenylene sulfide exhibits excellent thermal stability and chemical resistance and is suitable for thermoplastic extrusion processes.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • Latin America • North America
Features	• Chemical Resistant • Good Thermal Stability
Uses	• Film • Stock Material for Machining
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Extrusion

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.34		ASTM D792
Melt Mass-Flow Rate (MFR) ¹ (316°C/5.0 kg)	45	g/10 min	ASTM D1238
Water Absorption (24 hr, 23°C)	0.050	%	ASTM D570
Ash Content	0.3	wt%	ISO 3451-1
Volatiles (150°C)	< 0.3	wt%	

Mechanical

	Typical Value	Unit	Test method
Tensile Modulus	3400	MPa	ISO 527-2
Tensile Stress	75.0	MPa	ISO 527-2
Tensile Strain (Break)	6.0	%	ISO 527-2
Flexural Modulus	3400	MPa	ISO 178
Flexural Stress	130	MPa	ISO 178

Impact

	Typical Value	Unit	Test method
Notched Izod Impact			
3.18 mm	53	J/m	ASTM D256
--	4.0	kJ/m ²	ISO 180/A

Thermal

	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	160	°C	
1.8 MPa, Unannealed	95.0	°C	
Glass Transition Temperature	90.0	°C	ISO 11357-2
Vicat Softening Temperature	> 180	°C	ISO 306
Melting Temperature	280	°C	ISO 11357-3
CLTE - Flow			ASTM E831
-50 to 50°C	5.0E-5	cm/cm/°C	
100 to 200°C	1.2E-4	cm/cm/°C	

Ryton® QC160P

polyphenylene sulfide

Thermal	Typical Value	Unit	Test method
Thermal Conductivity	0.30	W/m/K	
Electrical	Typical Value	Unit	Test method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	24	kV/mm	ASTM D149
Dielectric Constant (25°C, 1 MHz)	3.20		ASTM D150
Dissipation Factor (25°C, 1 MHz)	2.0E-3		ASTM D150
Flammability	Typical Value	Unit	Test method
Flame Rating (1.6 mm, Tested by CP Chemical)	V-0		UL 94
Oxygen Index	44	%	ASTM D2863

Notes

Typical properties: these are not to be construed as specifications.

¹ Procedure B