

Ryton® R-4-232BL

polyphenylene sulfide

Ryton® R-4-232BL 40% glass fiber reinforced polyphenylene sulfide compound complies with United States Food and Drug Administration (FDA), NSF51, and European Union (EU 10/2011) regulations for use as a

component of articles intended for repeat use in contact with all types of foods. It has also been approved for drinking water systems by NSF61, KTW and ACS.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight
Features	• Food Contact Acceptable
Uses	• Appliance Components
Agency Ratings	• ACS Unspecified Rating • EU 10/2011 • FDA Food Contact, Unspecified Rating • KTW Unspecified Rating • NSF STD-51 • NSF STD-61
RoHS Compliance	• RoHS Compliant
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.68		ASTM D792
Molding Shrinkage			
Flow : 3.20 mm	0.20	%	
Across Flow : 3.20 mm	0.50	%	
Water Absorption (24 hr, 23°C)	0.020	%	ASTM D570

Mechanical

	Typical Value	Unit	Test method
Tensile Modulus	16100	MPa	ISO 527-2
Tensile Stress	145	MPa	ISO 527-2
Tensile Strain (Break)	1.1	%	ISO 527-2
Flexural Modulus	15900	MPa	ISO 178
Flexural Strength	230	MPa	ASTM D790
Compressive Strength	275	MPa	ASTM D695
Poisson's Ratio	0.43		ISO 527

Impact

	Typical Value	Unit	Test method
Notched Izod Impact			
3.18 mm	90	J/m	ASTM D256
--	8.7	kJ/m ²	ISO 180/A
Unnotched Izod Impact			
3.18 mm	370	J/m	ASTM D4812
--	26	kJ/m ²	ISO 180

Ryton® R-4-232BL

polyphenylene sulfide

Hardness	Typical Value	Unit	Test method
Rockwell Hardness			ASTM D785
M-Scale	104		
R-Scale	122		
Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed	265	°C	
CLTE			ASTM E831
Flow : 50 to 100°C	1.5E-5	cm/cm/°C	
Flow : 100 to 200°C	1.5E-5	cm/cm/°C	
Transverse : 50°C	4.0E-5	cm/cm/°C	
Transverse : 100 to 200°C	8.0E-5	cm/cm/°C	
Thermal Conductivity	0.31	W/m/K	
UL Temperature Rating	200 to 220	°C	UL 746B
Flammability	Typical Value	Unit	Test method
Flame Rating			UL 94
0.39 mm	V-0		
1.5 mm	5VA		

Notes

Typical properties: these are not to be construed as specifications.



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.