

# Ryton® R-7-190BL

## polyphenylene sulfide

Ryton® R-7-190BL glass fiber and mineral filled polyphenylene sulfide compound provides enhanced

strength and low maintenance molding using conventional molding equipment.

### General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Glass\Mineral
Features	• Chemical Resistant • Good Electrical Properties • Good Strength
RoHS Compliance	• RoHS Compliant
Appearance	• Black
Forms	• Pellets

### Physical

	Typical Value	Unit	Test method
Density <sup>1</sup>	2.00	g/cm <sup>3</sup>	ISO 1183
Water Absorption (24 hr, 23°C)	0.020	%	ASTM D570
Mold Shrinkage <sup>2</sup>			
Flow	0.20	%	
Transverse	0.40	%	

### Mechanical

	Typical Value	Unit	Test method
Tensile Strength	140	MPa	ISO 527
Tensile Elongation (Break)	1.0	%	ISO 527
Flexural Modulus	18000	MPa	ISO 178
Flexural Strength	220	MPa	ISO 178
Compressive Strength	275	MPa	ISO 604

### Impact

	Typical Value	Unit	Test method
Notched Izod Impact Strength	6.0	kJ/m <sup>2</sup>	ISO 180/A
Unnotched Izod Impact Strength	22	kJ/m <sup>2</sup>	ISO 180

### Thermal

	Typical Value	Unit	Test method
CLTE			ISO 11359-2
Flow : -50 to 50°C	1.5E-5	cm/cm/°C	
Flow : 100 to 200°C	1.5E-5	cm/cm/°C	
Transverse : -50 to 50°C	2.5E-5	cm/cm/°C	
Transverse : 100 to 200°C	6.5E-5	cm/cm/°C	
Thermal Conductivity	0.64	W/m/K	ASTM E1530
Heat Deflection Temperature - 1.8 MPa	265	°C	ASTM D648
Temperature Index	220 to 240	°C	UL 746B

# Ryton® R-7-190BL

## polyphenylene sulfide

Electrical	Typical Value	Unit	Test method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	18	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
25°C, 1 kHz	5.20		
25°C, 1 MHz	5.00		
Dissipation Factor			ASTM D150
25°C, 1 kHz	2.0E-3		
25°C, 1 MHz	2.0E-3		
Arc Resistance	185	sec	ASTM D495
Comparative Tracking Index (CTI)	250	V	UL 746
Insulation Resistance - 95% RH, 48 hr (90°C)	1.00E+13	ohms	

Flammability	Typical Value	Unit	Test method
Flame Rating (1.6 mm)	• •	V-0 5VA	UL 94

### Additional Information

Test specimen molding conditions: Stock temperature, 315-345°C; Mold temperature, 135°C

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Method A

<sup>2</sup> Measured on 102 mm x 102 mm x 3.2 mm plaques, edge gated.



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.