

# Ryton® R-7-220BL

## polyphenylene sulfide

Ryton® R-7-220BL glass fiber and mineral filled polyphenylene sulfide compound provides enhanced

mechanical strength after constant or repeated exposure to high temperature water.

### General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Glass\Mineral
Features	• Good Strength
Uses	• Automotive Applications
RoHS Compliance	• RoHS Compliant
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PPS-(GF+MD)65

### Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.95		ASTM D792
Molding Shrinkage			
Flow : 3.20 mm	0.20	%	
Across Flow : 3.20 mm	0.40	%	
Water Absorption (24 hr, 23°C)	0.020	%	ASTM D570

### Mechanical

	Typical Value	Unit	Test method
Tensile Strength			
--	152	MPa	ASTM D638
--	155	MPa	ISO 527-2
Tensile Elongation (Break)	1.0	%	ASTM D638 ISO 527-2
Flexural Modulus			
--	19300	MPa	ASTM D790
--	19000	MPa	ISO 178
Flexural Strength			
--	234	MPa	ASTM D790
--	240	MPa	ISO 178
Compressive Strength	295	MPa	ASTM D695
Poisson's Ratio	0.35		ISO 527

### Impact

	Typical Value	Unit	Test method
Notched Izod Impact			
3.18 mm	69	J/m	ASTM D256
--	8.0	kJ/m <sup>2</sup>	ISO 180/A

# Ryton® R-7-220BL

## polyphenylene sulfide

Impact	Typical Value	Unit	Test method
Unnotched Izod Impact			
3.18 mm	270	J/m	ASTM D4812
--	20	kJ/m <sup>2</sup>	ISO 180

Hardness	Typical Value	Unit	Test method
Rockwell Hardness			ASTM D785
M-Scale	99		
R-Scale	116		

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed	265	°C	
CLTE			ASTM E831
Flow : -50 to 50°C	1.5E-5	cm/cm/°C	
Flow : 100 to 200°C	1.0E-5	cm/cm/°C	
Transverse : -50 to 50°C	3.0E-5	cm/cm/°C	
Transverse : 100 to 200°C	7.0E-5	cm/cm/°C	
Thermal Conductivity	0.51	W/m/K	
UL Temperature Rating	220 to 240	°C	UL 746B

Electrical	Typical Value	Unit	Test method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength	18	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
25°C, 1 kHz	5.00		
25°C, 1 MHz	4.90		
Dissipation Factor			ASTM D150
25°C, 1 kHz	0.020		
25°C, 1 MHz	0.010		
Arc Resistance	185	sec	ASTM D495
Comparative Tracking Index (CTI)	175	V	UL 746
Insulation Resistance <sup>1</sup> (90°C)	1.0E+11	ohms	

Flammability	Typical Value	Unit	Test method
Flame Rating (1.6 mm)	• •	V-0 5VA	UL 94
Oxygen Index	62	%	ASTM D2863

Additional Information	Typical Value	Unit
Hydrolytic Stability <sup>2</sup>		
Tensile Strength Retained	> 75	%
Weight Gain	< 1.0	%

# Ryton<sup>®</sup> R-7-220BL

polyphenylene sulfide

---

## Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> 95%RH, 48 hr

<sup>2</sup> Test specimens aged 1000 hours in water at 140°C (284°F)



---

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva<sup>®</sup> family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.