

# Ryton® XE5515BL

## polyphenylene sulfide alloy

Ryton® XE5515BL 15% glass fiber reinforced polyphenylene sulfide alloy compound provides excellent

mechanical strength and chemical resistance at elevated temperatures and is suitable for extrusion or blow molding.

### General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Features	• Chemical Resistant • Good Strength
Uses	• Automotive Applications
RoHS Compliance	• RoHS Compliant
Appearance	• Black
Forms	• Pellets
Processing Method	• Blow Molding • Extrusion

### Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.42		ASTM D792
Melt Mass-Flow Rate (MFR) (316°C/5.0 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage			
Flow : 3.20 mm	0.50	%	
Across Flow : 3.20 mm	0.60	%	
Water Absorption (24 hr, 23°C)	0.010	%	ASTM D570

### Mechanical

	Typical Value	Unit	Test method
Tensile Modulus			
--	6210	MPa	ASTM D638
--	5800	MPa	ISO 527-2
Tensile Strength			
--	103	MPa	ASTM D638
--	110	MPa	ISO 527-2
Tensile Elongation (Break)	2.9	%	ASTM D638 ISO 527-2
Flexural Modulus			
--	5520	MPa	ASTM D790
--	5500	MPa	ISO 178
Flexural Strength			
--	159	MPa	ASTM D790
--	170	MPa	ISO 178
Poisson's Ratio	0.41		ISO 527

### Impact

	Typical Value	Unit	Test method
Notched Izod Impact			
3.18 mm	96	J/m	ASTM D256
--	10	kJ/m <sup>2</sup>	ISO 180/A

# Ryton® XE5515BL

polyphenylene sulfide alloy

Impact	Typical Value	Unit	Test method
Unnotched Izod Impact			
3.18 mm	690	J/m	ASTM D4812
--	45	kJ/m <sup>2</sup>	ISO 180
Hardness	Typical Value	Unit	Test method
Rockwell Hardness			ASTM D785
M-Scale	118		
R-Scale	87		
Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed	190	°C	
CLTE			ASTM E831
Flow : -50 to 50°C	3.0E-5	cm/cm/°C	
Flow : 100 to 200°C	2.0E-5	cm/cm/°C	
Transverse : -50 to 50°C	5.5E-5	cm/cm/°C	
Transverse : 100 to 200°C	9.0E-5	cm/cm/°C	
Thermal Conductivity	0.23	W/m/K	
Electrical	Typical Value	Unit	Test method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength	24	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
25°C, 1 kHz	3.60		
25°C, 1 MHz	3.50		
Dissipation Factor			ASTM D150
25°C, 1 kHz	2.0E-3		
25°C, 1 MHz	5.0E-3		
Arc Resistance	100	sec	ASTM D495
Comparative Tracking Index (CTI)	150	V	UL 746
Insulation Resistance <sup>1</sup> (90°C)	1.0E+13	ohms	
Flammability	Typical Value	Unit	Test method
Flame Rating (1.6 mm, Tested by CP Chemical)	V-0		UL 94
Oxygen Index	50	%	ASTM D2863

# Ryton® XE5515BL

polyphenylene sulfide alloy

---

## Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> 95%RH, 48 hr



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.