

Acudel® 22000

modified polyphenylsulfone

Acudel® 22000 is a modified polyphenylsulfone. It is a high-heat, high-performance resin formulation exhibiting very good hydrolytic stability, excellent resistance to acids and bases and good resistance to stress cracking under a broad range of chemical environments. In addition, Acudel® 22000 resin exhibits robust toughness and improved notch resistance compared to both Udel® polysulfone and Veradel® polyethersulfone, although slightly lower than that of neat Radel® polyphenylsulfone. In general, the performance profile of Acudel® 22000 resin falls between polysulfone and polyphenylsulfone.

In addition to its high mechanical and thermal performance attributes, Acudel® 22000 resin also offers very good electrical properties over a broad temperature range as well as inherent flame retardancy.

- Natural: Acudel® 22000 NT15
- Black: Acudel® 22000 BK937

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Features	• Acid Resistant • Base Resistant • Chemical Resistant • Flame Retardant • Good Thermal Stability	• Good Toughness • High ESCR (Stress Crack Resist.) • High Heat Resistance • Hydrolytically Stable
Uses	• Connectors • Fittings	• Piping • Plumbing Parts
Agency Ratings	• NSF STD-51	• NSF STD-61 ¹
RoHS Compliance	• RoHS Compliant	
Automotive Specifications	• ASTM D6394 SP0000A21640	• ASTM D6394 SP0412
Appearance	• Black	• Light Beige
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.28		ASTM D792
Melt Mass-Flow Rate (MFR) (380°C/2.16 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.70	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Water Absorption - (30 days)	0.90	%	ASTM D570

Mechanical

	Typical Value	Unit	Test method
Tensile Modulus	2690	MPa	ASTM D638
Tensile Strength	77.2	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	6.7	%	
Break	50	%	
Flexural Modulus	2760	MPa	ASTM D790
Flexural Strength (Yield)	108	MPa	ASTM D790

Acudel® 22000

modified polyphenylsulfone

Impact	Typical Value	Unit	Test method
Notched Izod Impact	110	J/m	ASTM D256
Tensile Impact Strength	368	kJ/m ²	ASTM D1822

Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load 1.8 MPa, Annealed, 3.18 mm	197	°C	ASTM D648

Electrical	Typical Value	Unit	Test method
Volume Resistivity	> 9.0E+15	ohms·cm	ASTM D257
Dielectric Strength (3.18 mm)	19	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.40		ASTM D150
Dissipation Factor (1 MHz)	8.0E-3		ASTM D150

Acudel® 22000


modified polyphenylsulfone

Injection	Typical Value	Unit
Drying Temperature	177	°C
Drying Time	2.5	hr
Processing (Melt) Temp	360 to 391	°C
Mold Temperature	138 to 163	°C
Injection Rate	Fast	
Screw Compression Ratio	2.2:1.0	

Injection Notes

Minimum recommended drying conditions are 2.5 hours at 350°F (177°C), or 4 hours at 300°F (149°C).

Isothermal Stress vs. Strain (ISO 11403-1)



Acudel® 22000

modified polyphenylsulfone

Notes

Typical properties: these are not to be construed as specifications.

¹ Tested at 82 °C (180 °F) (Commercial Hot)



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.