



SOLVAY
asking more from chemistry®

Effects of Steam Sterilization

Radel® PPSU

The ability to withstand repeated sterilization is a critical requirement for any material used in reusable medical devices. Steam sterilization is the most commonly used method and uses pressurized steam at 121 °C to 134 °C (250 °F to 273 °F) for up to 18 minutes. As with all sterilization techniques, medical devices are chemically washed and disinfected prior to autoclaving. They may also be exposed to other chemicals, such as morpholine, which are often added to central steam sterilization systems to inhibit corrosion in the lines. All things considered, it is one of the most severe sterilization environments for materials.

Suitable for especially harsh environments, Radel® PPSU (polyphenylsulfone) can be steam sterilized more than a thousand cycles without significant loss of properties. For over 15 years, this remarkably strong polymer has successfully replaced metals like stainless steel and aluminum in a wide variety of applications, including sterilization cases and trays, surgical and dental instrument handles, endoscopic devices, anesthesiology equipment, and joint replacement trials.

The success of Radel® PPSU can be attributed to several key performance attributes that are inherent to the polymer:

- High heat resistance
- Long-term thermal stability
- Resistance to prolonged hot water exposure
- Broad range of chemical resistance
- Exceptional toughness and durability

Thermal Properties

Radel® PPSU is an amorphous polymer with a glass transition temperature (T_g) of 220 °C (428 °F). This is the temperature at which the polymer transitions from a glassy state to a rubbery state and generally represents the upper temperature limit for short-term use.

Radel® PPSU has a heat deflection temperature (HDT) of 207 °C (405 °F) at 1.8 MPa (264 psi) as measured according to ASTM D638. This value is a relative measure of the polymer's ability to perform at an elevated temperature while supporting a load. In general, the maximum operating temperature for amorphous polymers is 5 °C to 10 °C (9 °F to 18 °F) below the HDT value.

Radel® PPSU also offers exceptional thermal stability, showing only 1 % weight loss in thermogravimetric analysis (TGA) testing at 496 °C (925 °F).

Hydrolytic Stability

Radel® PPSU has excellent retention of mechanical properties after long-term exposure to hot water. Test bars molded from Radel® PPSU were completely immersed in a 90 °C (194 °F) water bath for 16,000 hours (almost two years). The results in Table 1 show that Radel® PPSU retained over 85 % of its mechanical properties.

Table 1: Mechanical properties after 16,000-hour immersion in 90 °C (194 °F) water

Property	Retention [%]
Tensile strength	99.9
Tensile modulus	94.1
Elongation at yield	85.0
Notched Izod impact	117.6

Compatibility with Steam Additives

Tensile and flexural test specimens molded from Radel® PPSU were tested to determine as-molded mechanical properties. Additional specimens from the same resin lot were exposed to steam cycles at 132 °C (270 °F) with 50 ppm morpholine added. Each cycle consisted of a 2-minute heat up and pressurization, 30 minutes at 132 °C (270 °F) at 27 psi (186 kPa) steam pressure, 2-minute depressurization, and a 10-minute hold. Specimens were removed after 1,000 steam cycles and tested.

Test results are reported in Table 2. Although the tensile elongation value is reduced, it is still in the highly ductile region. This combined with the high notched Izod value indicate that practical toughness is still excellent and the finished parts will not become brittle.

Table 2: Mechanical properties before and after 1,000 steam cycles at 132 °C (270 °F) with 50 ppm morpholine

Property	Units	After 1,000 Cycles	
		As Molded	
Tensile strength	MPa	76	83
	psi	11,000	12,000
Tensile modulus	GPa	2.49	2.52
	kpsi	361	365
Tensile elongation	%	80	50
Flexural strength	MPa	130	126
	psi	18,800	18,300
Flexural modulus	GPa	2.44	2.52
	kpsi	354	365
Notched Izod impact	J/m	752	683
	ft-lb/in	14.1	12.8

Compatibility with Enzymatic Solutions

Test specimens, 127 mm x 13 mm x 3.2 mm (5 in. x 0.5 x 0.125 in.), molded from Radel® PPSU were exposed to steam cycles while under constant stress. Stress was achieved by hanging weights from one end of each test bar while the other end was supported as a cantilever beam. The applied loads resulted in stresses of 13.6 MPa (2,000 psi) and 27.2 MPa (4,000 psi).

Four commonly used enzymatic solutions were tested. For each of the enzyme solutions, test bars were soaked and then exposed to a 30-minute sterilization cycle with steam containing 50 ppm morpholine at 134 °C (273 °F). Test results after 22 steam-soak cycles are shown in Table 3. Radel® PPSU demonstrates excellent compatibility, even when the applied stress was doubled.

Table 3: Compatibility with enzymatic agents

Enzymatic Agent	Applied Stress		Radel® PPSU
	MPa	psi	
Enzol® 8 ml/l (1 oz/gal)	13.8	2,000	OK
	27.6	4,000	1 tiny craze
XMC-10 8 ml/l (1 oz/gal)	13.8	2,000	OK
	27.6	4,000	1 tiny craze
Klenzyme® 16 ml/l (2 oz/gal)	13.8	2,000	OK
	27.6	4,000	OK
Biozyme® 12 ml/l (1.5 oz/gal)	13.8	2,000	OK
	27.6	4,000	OK

Compatibility with Disinfectants

A separate study was conducted using steam without morpholine and four commonly used disinfectants. An applied strain of 0.8 %, which corresponds to a stress of about 21 MPa (3,000 psi), was applied to test bars in the same cantilever position as described earlier. Before each steam cycle, the test bars were disinfected with one of disinfectants. Even after 600 cycles, Radel® PPSU was not significantly affected by any of these disinfecting agents (see Table 4).

Table 4: Compatibility with disinfectants with 0.8 % applied stress after 600 cycles

Disinfectants	Radel® PPSU
Helipur® (phenol based)	OK
Kohrsolin®	OK
Neodisher® Septo (aldehyde based)	OK
Triton™ DF-16 (alcohol and tenside based)	OK

Exceptional Toughness and Durability

Test bars that were steam sterilized for 1,000 cycles at 132 °C (270 °F) with 50 ppm morpholine were tested for retention of practical toughness using an instrumented falling-dart impact test (Dynatup). Results are shown in Table 5.

Table 5: Practical toughness after 1,000 steam cycles at 132 °C (270 °F) with 50 ppm morpholine

Property	Units	As Molded	After 1,000 Cycles
Total energy	J	57.3	55.3
	ft-lb	42.3	40.8
Maximum load	N	5,900	5,800
	lb	1,330	1,303

During another study, flexural bars molded from Radel® PPSU were exposed to repeated steam sterilization while under constant stress. A weight was hung from the free end of the 127 mm (5 in.) bar while the other end was clamped in a cantilever beam arrangement. The weight created a stress of 6.9 MPa (1,000 psi). After 1,000 steam cycles, the test bars were virtually unaffected and showed no signs of mechanical failure such as cracking or crazing.

Conclusion

Steam sterilization, especially with amine corrosion inhibitors, degrades many plastic materials. Radel® PPSU has exceptional resistance to steam sterilization under stress, even in the presence of aggressive disinfectants and enzymatic cleansing agents. Additionally, the material's excellent mechanical properties and tremendous impact strength are not affected by long-term thermal aging or repeated chemical exposure. This combination of properties makes Radel® PPSU an excellent material for medical devices that are repeatedly disinfected and steam sterilized.

Since each application has its unique performance requirements and design criteria, it is important that specialized testing be conducted by the design engineer to evaluate the resin under conditions that best simulate the function of the component or system in its intended use.

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia Pacific

Material Safety Data Sheets (MSDS) are available by emailing us or contacting your sales representative. Always consult the appropriate MSDS before using any of our products. Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. All trademarks and registered trademarks are property of the companies that comprise Solvay Group or their respective owners.

© 2013 Solvay Specialty Polymers. All rights reserved. D 10/2009 | R 10/2013 | Version 3.2