

Udel® P-3500 LCD

polysulfone

Udel® P-3500 LCD is a very high molecular weight grade of polysulfone, and therefore offers the greatest toughness and chemical resistance of the available grades. It is well-suited for extrusion.

The advantages of Udel® P-3500 LCD are attributed to the lower level of cyclic dimer present in the polymer.

Polysulfone is a tough, rigid and transparent high-strength thermoplastic that is suitable for long-term use up to 300°F (149°C). It is resistant to oxidation and hydrolysis and withstands prolonged exposure to high temperatures and repeated sterilization.

Polysulfone is resistant to mineral acids, alkali, salt solutions, detergents and hydrocarbon oils. Contact with polar solvents such as ketones, chlorinated hydrocarbons and aromatic hydrocarbons should be avoided, as these types

of chemical compounds can cause stress cracking or solvate polysulfone resin.

Polysulfone is highly resistant to degradation by gamma or electron beam radiation but can be adversely affected by long term exposure to ultraviolet. Electrical properties of the polymer are very stable over a wide range of temperatures and after immersion in water or exposure to high humidity.

The resin is very safe for food contact uses. It complies with FDA 21 CFR 177, 1655 and may be used in articles intended for repeated use in contact with foods. Additionally, it is approved by the NSF, by the Department of Agriculture for contact with meat and poultry and the 3-A Sanitary Standards of the Dairy Association.

- Transparent: Udel P-3500 NT LCD

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Features	• Acid Resistant • Alcohol Resistant • Alkali Resistant • Chemical Resistant • Detergent Resistant • Good Dimensional Stability • Good Sterilizability	• Good Surface Finish • Good Toughness • High Heat Resistance • Hydrocarbon Resistant • Hydrolytically Stable • Steam Sterilizable
Uses	• Membranes	
Agency Ratings	• FDA 21 CFR 177.1655 • ISO 10993	• NSF STD-61 ¹
RoHS Compliance	• RoHS Compliant	
Appearance	• Natural Color	
Forms	• Pellets	
Processing Method	• Extrusion • Extrusion Blow Molding • Film Extrusion • Injection Blow Molding • Injection Molding	• Machining • Pipe Extrusion • Profile Extrusion • Sheet Extrusion • Thermoforming

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.24		ASTM D792
Melt Mass-Flow Rate (MFR) (343°C/2.16 kg)	3.0 to 5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.70	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570

Udel® P-3500 LCD

polysulfone

Mechanical	Typical Value	Unit	Test method
Tensile Modulus	2480	MPa	ASTM D638
Tensile Strength (Break)	70.3	MPa	ASTM D638
Tensile Elongation (Break)	50 to 100	%	ASTM D638
Flexural Modulus	2690	MPa	ASTM D790
Flexural Strength	106	MPa	ASTM D790
Impact	Typical Value	Unit	Test method
Notched Izod Impact	69	J/m	ASTM D256
Tensile Impact Strength	420	kJ/m ²	ASTM D1822
Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load 1.8 MPa, Unannealed	174	°C	ASTM D648
CLTE - Flow	5.6E-5	cm/cm/°C	ASTM D696
Electrical	Typical Value	Unit	Test method
Volume Resistivity	3.0E+16	ohms·cm	ASTM D257
Dielectric Strength	17	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
60 Hz	3.03		
1 kHz	3.04		
1 MHz	3.02		
Dissipation Factor			ASTM D150
60 Hz	7.0E-3		
1 kHz	1.0E-3		
1 MHz	6.0E-3		

Udel® P-3500 LCD

polysulfone

Injection Notes

UDEL P-3500 polysulfones may be dried before preparing solutions. Pellets can be dried in a circulating hot air oven, by spreading the pellets on trays to a 1-2 inch depth and drying for 3.5 hours at 257 to 325°F (135 to 163°C).

Extrusion	Typical Value	Unit
Drying Temperature	135 to 163	°C
Drying Time	3.5	hr
Cylinder Zone 1 Temp.	302	°C
Cylinder Zone 5 Temp.	316 to 338	°C
Melt Temperature	316 to 371	°C

Notes

Typical properties: these are not to be construed as specifications.

¹ Tested at 82 °C (180 °F) (Commercial Hot)



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.