

Algoflon® DF 130 F

polytetrafluoroethylene

Algoflon® DF 130 F is a white fine coagulated powder and is produced without any intentional use or addition of PFOA. It is designed for paste extrusion and is particularly recommended for manufacture of porous items and fibers. It can also be used for production of pipe liners (large diameters).

Algoflon® DF 130 exhibits high both green strength and stretchability.

Main features of Algoflon® DF 130 F include:

- High green strength
- High and homogenous stretchability

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• North America
Features	• Chemical Resistant • Good Processing Stability	• Good Thermal Stability • Low Friction
Uses	• Aerospace Applications • Automotive Applications • Electrical/Electronic Applications • Fibers	• Industrial Applications • Membranes • Tape • Wire & Cable Applications
Agency Ratings	• FDA 21 CFR 177.1550	
Appearance	• White	
Forms	• Powder	

Physical	Typical Value	Unit	Test method
Specific Gravity	2160		ASTM D792
Average Particle Size	600	µm	Internal Method
Bulk Density	500	g/l	ASTM D4895
Stretchability	1500	%	Internal Method

Mechanical	Typical Value	Unit	Test method
Tensile Strength	30.0	MPa	ASTM D4895
Elongation at Break	300	%	ASTM D4895

Thermal	Typical Value	Unit	Test method
Thermal Instability Index	< 15.0		ASTM D4895

Additional Information	Typical Value	Unit	Test method
Reduction Ratio - range	30.0 to 300		Internal Method
Rheometer Pressure - @ RR 100:1	9.50	MPa	ASTM D4895

Algoflon® DF 130 F

polytetrafluoroethylene

Processing

- Algoflon® DF 130 F is processed according to methods conventionally used for paste extrusion. Initially the powder is mixed with a lubricant to produce a paste. This is then compacted into a preform and extruded through a finishing die using a ram extruder. Further processing as calendaring, removal of lubricant and stretching can then be carried out to make final products such as tapes, cords and other general porous items.
- The mixing, preforming, extrusion and heating and stretching steps must all be carefully controlled to produce defect free products.

Storage and Handling

- Algoflon® PTFE fine coagulated powders must be stored and handled carefully to avoid excessive shearing and particle fibrillation. Fibrillation is irreversible and damaged particles can appear as defects in manufactured articles. PTFE fine coagulated powders must be handled below 19°C because above this temperature the powders are softer and can be more easily laminated. It is recommended sieving of powders below 19°C before adding lubricant. Strong vibrations and shocks must be avoided as much as possible for prevent lumps formation. Storage and transportation should be carried out in the range 5 - 19°C. Moreover, the powders must be stored in a dry room because the absorption of moisture could negatively affect its processing. Storage and handling facilities should be clean since even very small foreign particles can cause defects in finished products. Keep resin drums closed and clean. Good housekeeping and careful handling are essential.
- Storage and transportation should be carried out in the range 5 - 19°C. Moreover, the powders must be stored in a dry room because the absorption of moisture could negatively affect its processing.
- Storage and handling facilities should be clean since even very small foreign particles can cause defects in finished products. Keep resin drums closed and clean. Good housekeeping and careful handling are essential.

Safety and Toxicology

- Before using Algoflon® PTFE fine coagulated powders consult the product Material Safety Data Sheet and follow all label directions and handling precautions. As with all PTFE materials, handling and processing should only be carried out in well ventilated areas. Vapor extractor units should be installed above processing equipment. Fumes must not be inhaled and eye and skin contact ought to be avoided. In case of skin contacts wash with soap and water. In case of eye contact flush with water immediately and seek medical help. Do not smoke in areas contaminated with powder, vapor or fumes. See Material Safety Data Sheet for detailed advice on waste disposal methods.

Packaging

- Algoflon® DF 130 F is packaged in 25 kg non returnable drums.

Additional Technical Information

- For Material Safety Data Sheet or additional technical information consult your Solvay Specialty Polymers sales representative, or contact us by e-mail.
-