

Polymist® XPP 535

polytetrafluoroethylene

Polymist® XPP 535 a white PTFE micronized powder composed of discrete particles.

Designed for use in critical engineering and high end performance coatings and inks, Polymist® XPP 535 will improve non-stick properties and mar and abrasion resistance as well as slip and rub resistance.

Main Polymist® XPP 535 features are:

- Improved abrasion, scratch and rub resistance
- Increased slip and surface lubricity
- Reduced blocking
- Better chemical resistance
- Increased temperature resistance
- Gloss retention

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Uses	• Additive
Appearance	• White
Forms	• Powder

Physical

	Typical Value	Unit	Test method
Bulk Density	325	g/l	ASTM D4895
Particle Size - (D50/D99)	• 3.80 • 10.0	μm	Internal Method
Specific Surface Area	3.0	m ² /g	Internal Method

Additional Information

	Typical Value	Unit	Test method
Grind in Oil - NPIRI	2.00		NPIRI
Melt Temperature	320 to 330	°C	ASTM D3418

Processing

- Polymist® XPP 535 is used as additives in paints and coatings where improvements in non-stick, mar resistance, slip, chemical resistance, and moisture repelling characteristics are desired.
- Polymist® XPP 535 may be used independently as an additive or in combination with polyethylene waxes. The PTFE content at the surface layer is required in order to impart the properties of PTFE to the coating, substantially. Extreme environmental demands on greases, such as those experienced in the automotive industry (i.e. wide temperature ranges and heavy loads) can be accommodated by the addition of Polymist® XPP 535 micronized powders.
- Polymist® XPP 535 can be dispersed easily at room temperature, and it doesn't agglomerate at temperatures used during formulation or printing. Chemical inertness and improved temperature resistance give ink formulators the opportunity to use a variety of solvents without adverse chemical reactions.

Storage and Handling

- The usual precautions for safe storage and handling of Polymist® XPP 535 should be taken according to material safety documentation and experience. There will be no chemical deterioration of the Polymist® XPP 535 during proper storage.
- Shelf life of Polymist® XPP 535 micronized powders will vary depending upon whether the recommended storage conditions are maintained and whether the material remains free from foreign contamination during storage time (not exposed to dirt, dust, water or other chemicals). The material should remain sealed in the original containers and storage conditions should provide for protection from temperature extremes as well as rain, snow or other wet environments (or such conditions which may damage the storage containers in which the product is stored).

Safety and Toxicology

- Before using PTFE Polymist® XPP 535 micronized powders consult the product Material Safety Data Sheet and follow all label directions and handling precautions.
- As with all PTFE materials, handling and processing should only be carried out in well ventilated areas. Vapor extractor units should be installed above processing equipment. Fumes must not be inhaled and eye and skin contact ought to be avoided. In case of skin contact wash with soap and water. In case of eye contact flush with water immediately and seek medical help. Do not smoke in areas contaminated with powder, vapor or fumes. See Material Safety Data Sheet for detailed advice on waste disposal methods.

Packaging

- Polymist® XPP 535 is packaged in 25 kg non returnable drums. Each drum has one bag liner made of polyethylene resin.

Notes

Typical properties: these are not to be construed as specifications.