

Solef® 5120

polyvinylidene fluoride

Solef® 5120 PVDF is a medium viscosity grade that gives improved adhesion ideal for its usage in lithium batteries.

General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Features	• Good Adhesion	• Medium Viscosity
Uses	• Batteries	• Binder

Physical	Typical Value	Unit	Test method
Density	1.75 to 1.78	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/21.6 kg)	< 3.0	g/10 min	ISO 1133
Water Absorption ¹ (24 hr, 23°C)	< 0.20	%	ASTM D543

Mechanical	Typical Value	Unit	Test method
Tensile Modulus ² (23°C)	1000 to 1500	MPa	ASTM D638

Thermal	Typical Value	Unit	Test method
Glass Transition Temperature	-40.0	°C	DSC
Melting Temperature	160 to 168	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	124 to 130	°C	ASTM D3418
Heat of Fusion ³	38.0 to 48.0	J/g	ASTM D3418
Thermal Stability ⁴	> 375	°C	TGA

Electrical	Typical Value	Unit	Test method
Surface Resistivity ⁵	> 1.0E+14	ohms	ASTM D257
Volume Resistivity ⁶	> 1.0E+14	ohms·cm	ASTM D257

Additional Information

Intrinsic Viscosity: 0.15 - 0.25 l/g

Solef® 5120

polyvinylidene fluoride

Notes

Typical properties: these are not to be construed as specifications.

¹ 30g

² 1.0 mm/min

³ 80°C to end of melting

⁴ @ 1% weight loss

⁵ Voltage < 1V, after 2 min - 500 V @ 23°C

⁶ Intensity = 10 mA, after 2 min @ 23°C



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.