

Solef® 60512/0550 and 60512/0150

polyvinylidene fluoride

Solef® 60512/0550 and Solef® 60512/0150 are PVDF grades compounded with PTFE for extrusion of anti-wear tapes.

General

Material Status	• Commercial: Active
Availability	<ul style="list-style-type: none"> • Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Features	• Copolymer
Uses	• Tape

Physical	Typical Value	Unit	Test method
Density	1.80 to 1.82	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/10.0 kg)	2.0 to 4.5	g/10 min	ASTM D1238
Water Absorption (24 hr, 23°C)	< 0.040	%	ISO 62

Mechanical	Typical Value	Unit	Test method
Tensile Modulus ¹ (23°C, 1.50 mm)	1100 to 1350	MPa	ASTM D638
Tensile Strength ²			ASTM D638
Yield, 23°C, 1.50 mm	30.0 to 40.0	MPa	
Break, 23°C, 1.50 mm	30.0 to 40.0	MPa	
Tensile Elongation ²			ASTM D638
Yield, 23°C, 1.50 mm	8.0 to 12	%	
Break, 23°C, 1.50 mm	50 to 300	%	
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.10 to 0.20		
vs. Itself - Static	0.050 to 0.20		
Taber Abrasion Resistance			ASTM D4060
1000 Cycles, 1000 g, CS-10 Wheel	5.00 to 10.0	mg	

Thermal	Typical Value	Unit	Test method
Melting Temperature	170 to 174	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	144 to 148	°C	ASTM D3418
Crystallization Heat	38.0 to 48.0	J/g	ASTM D3417
Heat of Fusion - (80°C to end of melting)	41.0 to 50.0	J/g	ASTM D3417

Solef® 60512/0550 and 60512/0150

polyvinylidene fluoride

Notes

Typical properties: these are not to be construed as specifications.

¹ Type V, 1.0 mm/min

² Type V, 50 mm/min



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.