

# Solef® 9007

## polyvinylidene fluoride

Solef® 9007 PVDF homopolymer has low viscosity and is used in film extrusion and injection molding.

### General

Material Status	• Commercial: Active	
Availability	• Africa & Middle East • Asia Pacific • Europe	• Latin America • North America
Features	• Homopolymer	• Low Viscosity
Processing Method	• Film Extrusion	• Injection Molding

### Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.75 to 1.80		ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
230°C/3.8 kg	16 to 26	g/10 min	
230°C/5.0 kg	20 to 38	g/10 min	
Molding Shrinkage - Flow	2.0 to 3.0	%	
Water Absorption (24 hr, 23°C)	< 0.040	%	ASTM D570

### Mechanical

	Typical Value	Unit	Test method
Tensile Modulus <sup>1</sup> (23°C, 2.00 mm)	1400 to 2200	MPa	ASTM D638
Tensile Strength <sup>2</sup>			ASTM D638
Yield, 23°C, 2.00 mm	45.0 to 60.0	MPa	
Break, 23°C, 2.00 mm	30.0 to 50.0	MPa	
Tensile Elongation <sup>2</sup>			ASTM D638
Yield, 23°C, 2.00 mm	5.0 to 10	%	
Break, 23°C, 2.00 mm	20 to 300	%	
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.15 to 0.35		
vs. Itself - Static	0.20 to 0.40		
Taber Abrasion Resistance			ASTM D4060
1000 Cycles, 1000 g, CS-10 Wheel	5.00 to 10.0	mg	

### Impact

	Typical Value	Unit	Test method
Charpy Notched Impact Strength <sup>3</sup>			ASTM D6110
23°C, 4.00 mm	60.0 to 120	J/m	

### Hardness

	Typical Value	Unit	Test method
Durometer Hardness (Shore D, 1 sec, 2.00 mm)	73 to 80		ASTM D2240

### Thermal

	Typical Value	Unit	Test method
Glass Transition Temperature	-40.0	°C	ASTM D4065
Melting Temperature	162 to 168	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	133 to 140	°C	ASTM D3418

# Solef® 9007

polyvinylidene fluoride

Thermal	Typical Value	Unit	Test method
Crystallization Heat	53.0 to 60.0	J/g	ASTM D3418
Heat of Fusion	53.0 to 60.0	J/g	ASTM D3418

  

Electrical	Typical Value	Unit	Test method
Surface Resistivity	> 1.0E+14	ohms	ASTM D257
Volume Resistivity	> 1.0E+14	ohms·cm	ASTM D257
Dielectric Strength (23°C, 1.00 mm)	20 to 25	kV/mm	ASTM D149
Dielectric Constant (23°C, 1 kHz)	7.00 to 10.0		ASTM D150

  

Flammability	Typical Value	Unit	Test method
Flame Rating (0.100 mm)	V-0		UL 94
Oxygen Index (3.00 mm)	44	%	ASTM D2863

## Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Type IV, 1.0 mm/min

<sup>2</sup> Type IV, 50 mm/min

<sup>3</sup> 2 m/s



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.