

# Solef® 90615/2002

## polyvinylidene fluoride

Solef® 90615 PVDF copolymer has high viscosity of the melt and it is a grade for offshore piping.

### General

Material Status	• Commercial: Active
Availability	<ul style="list-style-type: none"> <li>• Africa &amp; Middle East</li> <li>• Asia Pacific</li> <li>• Europe</li> <li>• Latin America</li> <li>• North America</li> </ul>
Features	• Copolymer
Uses	• High Viscosity
	• Piping

Physical	Typical Value	Unit	Test method
Density	1.75 to 1.80	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/10.0 kg)	0.50 to 2.0	g/10 min	ASTM D1238
Water Absorption (24 hr, 23°C)	< 0.040	%	ASTM D570

Mechanical	Typical Value	Unit	Test method
Tensile Modulus <sup>1</sup> (23°C, 1.50 mm)	800 to 1000	MPa	ASTM D638
Tensile Strength <sup>2</sup>			ASTM D638
Yield, 23°C, 1.50 mm	25.0 to 35.0	MPa	
Break, 23°C, 1.50 mm	40.0 to 55.0	MPa	
Tensile Elongation <sup>2</sup>			ASTM D638
Yield, 23°C, 1.50 mm	15 to 20	%	
Break, 23°C, 1.50 mm	> 200	%	
Coefficient of Friction			ASTM D1894
vs. Itself - Dynamic	0.25 to 0.35		
vs. Itself - Static	0.20 to 0.40		
Taber Abrasion Resistance			ASTM D4060
1000 Cycles, 1000 g, CS-17 Wheel	4.00 to 8.00	mg	

Impact	Typical Value	Unit	Test method
Charpy Notched Impact Strength (23°C)	110	kJ/m <sup>2</sup>	ISO 179/1eA

Hardness	Typical Value	Unit	Test method
Durometer Hardness (Shore D, 2.00 mm)	70		ASTM D2240

Thermal	Typical Value	Unit	Test method
Heat Deflection Temperature			ISO 75-2/B
0.45 MPa, Unannealed	98.0	°C	
Glass Transition Temperature	-40.0	°C	ASTM D4065
Vicat Softening Temperature	95.0	°C	ISO 306 <sup>3</sup>
Melting Temperature	169 to 174	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	141 to 145	°C	ASTM D3418
CLTE - Flow (-30 to 50°C)	1.5E-4 to 1.8E-4	cm/cm/°C	ASTM E831

# Solef® 90615/2002

## polyvinylidene fluoride

Thermal	Typical Value	Unit	Test method
Specific Heat			ASTM E968
23°C	1230	J/kg/°C	
100°C	1630	J/kg/°C	
Thermal Conductivity (23°C)	0.21	W/m/K	ASTM C177
Crystallization Heat	38.0 to 46.0	J/g	ASTM D3417
Heat of Fusion	40.0 to 48.0	J/g	ASTM D3417
Electrical	Typical Value	Unit	Test method
Surface Resistivity	> 1.0E+14	ohms	ASTM D257
Volume Resistivity	> 1.0E+14	ohms·cm	ASTM D257

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Type IV, 1.0 mm/min

<sup>2</sup> Type IV, 50 mm/min

<sup>3</sup> Rate A (50°C/h), Loading 2 (50 N)



Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2019 Solvay Specialty Polymers. All rights reserved.