



TECHNYL 2912GMH7-P BLACK

Description

TECHNYL® 2912GMH7-P BLACK is a blend of polyamide 66 and polyamide 6, reinforced with 63% of glass fiber, UV stabilized, for injection molding.

This product is available in black.

Benefits

This grade offers UV stabilization and an excellent combination between mechanical properties and surface aspect.

Applications

It is used in all sectors of industry, widely used for :

- Automotive part: Outside mirror base plate

Key Properties

Mechanical performance
UV stabilised

Regional Availability

Asia / Pacific

Properties

Typical values of properties are for black grades

| | Standards | Unit | Values | |
|---|-----------------|-------|-----------------|-------|
| | | | d.a.m. | Cond. |
| Physical | | | | |
| Density | ASTM D-792 | g/cm3 | 1,72 | |
| | ISO 1183/A | g/cm3 | 1,68 | |
| Molding shrinkage Parallel | RHODIA | % | 0,25 | |
| Molding shrinkage normal or perpendicular | RHODIA | % | 0,45 | |
| Mechanical | | | | |
| Tensile strength at yield | ASTM D-638 | MPa | 215 | |
| | ISO 527 Type 1A | MPa | 210 | |
| Elongation at break | ASTM D-638 | % | 1,50 | |
| | ISO 527 Type 1A | % | 2 | |
| Flexural modulus | ASTM D-790 | MPa | 17000 | |
| | ASTM D-790 | MPa | 16500 | |
| Flexural maximum stress | ASTM D-790 | MPa | 310 | |
| | ISO 178 | MPa | 330 | |
| Izod notched impact strength | ASTM D256 | J/m | 215 | |
| | ISO 180/1A | kJ/m2 | 11 | |
| Flammability | | | | |
| Flammability (Thickness: 3,2 mm) | ISO 1210 / UL94 | | HB | |
| Thermal | | | | |
| Melting Temperature | ISO 11357 | °C | 240 - 262 | |
| Heat deflection temperature (1,8 MPa) | ASTM D-648 | °C | 220 | |
| | ISO 75/Af | °C | 215 | |
| Specific | | | | |
| Identification code | | | (PA66+PA6)-GF63 | |

d.a.m. = dry as moulded
Cond = conditioned

Disclaimer

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANDABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.

Processing Guide

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment.

Recommended Maximum water content: 0,2 %

Drying conditions: 80 °C

Recommended moulding conditions

Barrel Temperatures:

| | |
|---------------------|--------------|
| - feed zone | 270 - 280 °C |
| - compression zone | 275 - 285 °C |
| - mixing zone | 280 - 290 °C |
| Mould temperatures: | 70 - 100 °C |

Steel advice for tools For reinforced polyamide (glass fibre, glass sphere, mineral fibre...), Solvay recommends the use of steel with a high content of Carbon and purified for polishing to avoid or limit the abrasion. For example: Z38CDV5W or Z160CDV12.

Safety information

Detailed information regarding safety are available on the safety data sheet (SDS).
SDS is sent with the first material order, or available by contacting our customer services

Regulations compliance

Grades produced or imported in Europe comply with directive 453/2010/EC, which amends REACH directive 1907/2006/EC

This grade complies with RoHS directive 2002/95/EC

Unless specified, this grade is not suitable for food contact, medical devices or toy applications

Customer services

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

You can find more information on Solvay Product range by on Technyl.com and the link to the product finder and brochures at the following address:
<http://www.technyl.com/en/download/brochures/index.html>