



TECHNYL A 218 S30

Description

TECHNYL® A 218 S30 is a Polyamide PA66, reinforced with 30% of glass spheres, heat stabilised, for injection moulding. This product is available in natural and black colours.

Key Properties

Isotropic shrinkage
Excellent combination between thermal & mechanical properties

Benefits

This grade offers an excellent combination between thermal and mechanical properties.

Applications

It is recommended for mechanical components which require a very good surface finish with low warpage, and good compression strength. (bearing housings).

Properties

Typical values of properties are for black grades

	Standards	Unit	Values	
			d.a.m.	Cond.
Physical				
Water absorption(24h at 23°C)	ISO 62	%	0,75	
Density	ISO 1183/A	g/cm3	1,37	
Mechanical				
Tensile Modulus	ISO 527 Type 1A	MPa	4500	2500
Tensile strength at yield	ISO 527 Type 1A	MPa	80	
Tensile strength at break	ISO 527 Type 1A	MPa	80	60
Elongation at yield	ISO 527 Type 1A	%	4	
Elongation at break	ISO 527 Type 1A	%	9	12
Flexural modulus	ISO 178	MPa	3850	1900
Charpy notched impact strength	ISO 179/1eA	kJ/m2	3,5	5
Charpy unnotched impact strength	ISO 179/1eU	kJ/m2	20	NB
Izod notched impact strength	ISO 180/1A	kJ/m2	2,5	5
Flammability				
Limit Oxygen Index	ISO 4589		25	
Thermal				
Melting Temperature	ISO 11357	°C	263	
Electrical				
Comparative tracking index (Sol A)	IEC 60112	V	450	
Dielectric strength	IEC 60243	kV/mm	30	26
Dissipation factor	IEC 60250		0,020	0,110
Surface resistivity	IEC 60093	Ohm	5E 14	
Volume resistivity	IEC 60093	Ohm/cm	5E 14	
Specific				
Identification code			PA66-GB30	

d.a.m. = dry as moulded

Cond = conditioned

Disclaimer

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANDABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.

Processing Guide

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment.

Recommended Maximum water content: 0,2 %

Drying conditions: 80 °C

Recommended moulding conditions

Barrel Temperatures:

- feed zone	270 - 280 °C
- compression zone	275 - 285 °C
- mixing zone	280 - 290 °C
Mould temperatures:	70 - 100 °C

Steel advice for tools For reinforced polyamide (glass fibre, glass sphere, mineral fibre...), Solvay recommends the use of steel with a high content of Carbon and purified for polishing to avoid or limit the abrasion. For example: Z38CDV5W or Z160CDV12.

Safety information

Detailed information regarding safety are available on the safety data sheet (SDS).
SDS is sent with the first material order, or available by contacting our customer services

Regulations compliance

Grades produced or imported in Europe comply with directive 453/2010/EC, which amends REACH directive 1907/2006/EC

This grade complies with RoHS directive 2002/95/EC

Unless specified, this grade is not suitable for food contact, medical devices or toy applications

Customer services

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

You can find more information on Solvay Product range by on Technyl.com and the link to the product finder and brochures at the following address:
<http://www.technyl.com/en/download/brochures/index.html>