



DEXFLEX 930

DESCRIPTION:

DEXFLEX® 930 is a thermoplastic olefinic elastomer (TPO) designed for large automotive exterior applications that require high flow for excellent processability, ductile impact properties at low temperatures, and good paint adhesion.

APPLICATIONS:

Bumper fascias and exterior trim

PROPERTY	TYPICAL VALUE	UNITS	TEST METHOD
PHYSICAL			
Density	0.95	g/cm ³	ISO 1183
As Molded Mold Shrinkage	.007 - .010	mm/mm	ISO 294
After Bake Mold Shrinkage	.009 - .012	mm/mm	ISO 294
Melt Flow Rate	21.0	g/10 min	ISO 1133
MECHANICAL			
Flexural Modulus	940	MPa	ISO 178 80x10x4mm specimen, 2 mm/min
Tensile Strength at Yield	15.0	MPa	ISO 527-1 and 527-2 150x10x4 mm specimen, 50 mm/min
Multiaxial Impact Strength @ 23°C	18	J	ASTM D3763 2.2 m/s
THERMAL			
CLTE	7.0 x 10 ⁻⁵	mm/mm/°C	ASTM E228 -30°C to 80°C

01/26/05

Solvay
Engineered Polymers
1200 Harmon Road
Auburn Hills, MI 48326
Phone: (248) 391-9500
Fax: (248) 391-9501

DEXFLEX®, DEXPRO®, ONTEX®, and SEQUEL® are registered trademarks and RESPOND™ is a trademark of Solvay Engineered Polymers. To our actual knowledge, the information contained herein is accurate as of the date hereof. However, neither Solvay Engineered Polymers nor any of its affiliates makes any warranty, express or implied, nor accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk, and does not relate to the use of any product in combination with any other substance or in any process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use, and whether any patents are infringed. The above information gives typical properties only and is not to be used for specification purposes.