



DEXFLEX E600

DESCRIPTION:

DEXFLEX[®] E600 thermoplastic olefinic elastomer (TPO) is an extrusion-grade material that can be readily processed into a variety of sheet and profile products. This material can be supplied with or without UV stabilizers.

APPLICATIONS:

Industrial exterior applications that require toughness and colorability

PROPERTY	TYPICAL VALUE	UNITS	ASTM METHOD
PHYSICAL			
Hardness	55	Shore D	D-2240
Specific Gravity	0.90		D-792
Melt Flow Rate (230°C, 2.16 kg load)	0.95	g/10 min	D-1238 Procedure A
MECHANICAL			
Flexural Modulus	60,000 (414)	psi (MPa)	D-790 I.B., TAN, 0.5 in/min
Tensile Strength @ Yield	3,000 (21)	psi (MPa)	D-638 IV, 2 in/min
Elongation @ Break	750	%	D-638
Gardner Impact @ 23°C	>320 (36)	in-lb (J)	D-5420-96
@ -30°C	>320 (36)	in-lb (J)	
THERMAL			
CLTE (-30°C to 80°C)	5.0 x 10 ⁻⁵ (9.0 x 10 ⁻⁵)	in/in/°F (mm/mm/°C)	D-696, Modified

01/2005

Solvay
Engineered Polymers
1200 Harmon Road
Auburn Hills, MI 48326
Phone: (248) 391-9500
Fax: (248) 391-9501

DEXFLEX[®], DEXPRO[®], ONTEX[®], and SEQUEL[®] are registered trademarks and RESPOND[™] is a trademark of Solvay Engineered Polymers. To our actual knowledge, the information contained herein is accurate as of the date hereof. However, neither Solvay Engineered Polymers nor any of its affiliates makes any warranty, express or implied, nor accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk, and does not relate to the use of any product in combination with any other substance or in any process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use, and whether any patents are infringed. The above information gives typical properties only and is not to be used for specification purposes.