



DEXPRO® 515

DESCRIPTION:

DEXPRO® 515 is a 15% mineral filled impact modified polypropylene for injection molding processes. This product can be supplied in natural or pre-colored, with or without UV protection.

NOMINAL PROPERTIES:

PROPERTY	TYPICAL VALUE	UNITS	TEST METHODS
PHYSICAL			
Mineral Filler	15	%	
Specific Gravity	1.00	—	ISO 1183
Melt Flow Rate, 230°C / 2.16 kg	28	dg/min	ISO 1133
MECHANICAL			
Tensile Stress at Yield	26	MPa	ISO 527-1, 50mm/min
Tensile Elongation at Yield	< 10	%	ISO 527-1, 50mm/min
Tensile Elongation at Break	-	%	ISO 527-1, 50mm/min
Flexural Modulus, +23°C (4mm thickness)	2,200	MPa	ISO 178, 2 mm/min
THERMAL			
DTUL, Heat Distortion Temperature			
0.45 MPa applied stress, un-annealed	105	°C	ISO 75
1.8 MPa applied stress, un-annealed	60	°C	ISO 75
Flammability (FMVSS 302)	< 100	mm/min	ISO 3795 / SAE J369
IMPACT			
Multi-Axial Instrumented Impact			
at +23°C, 6.7 m/s (15 mph)	6	J at max load	ASTM D 3763
Notched Izod Impact, at +23°C	60	J/m	ASTM D 256 A
Notched Izod Impact, at +23°C	5	kJ/m ²	ISO 180/1eA
MOLD SHRINKAGE			
As Molded	1.1 +/- 0.2	%	ISO 294-4
After Bake, 48hrs / 80°C	1.4 +/- 0.2	%	ISO 294-4

Mold shrinkage is measured on laboratory injection molded flat plaque, 150 x 100 x 3.2 mm, and is not necessarily representative of actual field data. The part wall thickness, gate type and location, flow length and paint oven temperature affect final part dimensions. Please contact your Solvay Engineered Polymers representative before any tools are cut.

Tests are made in accordance with the current issue of the ISO, ASTM, or other cited test methods. Test data reported here are nominal values measured on injection molded plaques and test bars.

Drying:

Pellet drying is generally unnecessary for DEXPRO® engineered polyolefin materials. However, drying may help to improve the aesthetic appearance by removing surface moisture. Drying with dehumidified air (-20°C dew point or lower) at 50-80°C for 2 to 6 hours is generally sufficient to remove any residual moisture to below 0.05 wt%.

For further information, please contact Solvay Engineered Polymers.

Solvay
Engineered Polymers
1200 Harmon Road
Auburn Hills, MI 48326
Phone: (248) 391-9500
Fax: (248) 391-9501

DEXFLEX®, DEXPRO®, ONTEX® and SEQUEL® are registered trademarks and RESPOND™ is a trademark of Solvay Engineered Polymers. To our actual knowledge, the information contained herein is accurate as of the date hereof. However, neither Solvay Engineered Polymers nor any of its affiliates makes any warranty, express or implied, nor accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk, and does not relate to the use of any product in combination with any other substance or in any process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use, and whether any patents are infringed. The above information gives typical properties only and is not to be used for specification purposes.