



NexPrene[®] 9080A

DESCRIPTION:

NexPrene[®] 9080A thermoplastic vulcanizate is a fully crosslinked EPDM/PP compound. It is designed to replace thermoset elastomers, such as EPDM or polychloroprene, and traditional thermoplastic TPVs. NexPrene[®] 9080A provides the performance of vulcanized rubber with the advantage of low-cost thermoplastic processing.

APPLICATIONS:

Suitable for applications requiring flexibility in the following markets: automotive, appliance, business machines, construction, consumer products, electrical & electronics, fluid delivery, hardware, and medical devices.

| PROPERTY | TYPICAL VALUE | UNITS | TEST METHOD |
|---|---------------|-------------|----------------|
| PHYSICAL | | | |
| Hardness: Injection Molded, 5 sec | 80 | Shore A | ISO 868 |
| Specific Gravity 23°C | 0.96 | g/cc | ISO 1183 |
| Oil Resistance 125°C, 70 hrs | 70 | % vol swell | ISO 1817 |
| Compression Set 24 hr @ 23°C 70 hr @ 125°C | 23 60 | % | ISO 815 |
| Brittle Point | <-50 | °C | ISO 812 |
| Ozone Resistance 500 hr, 100 pphm O ₃ conc. | Good | | ASTM D-1149 |
| MECHANICAL | | | |
| Tensile Strength 23°C, 550 mm/min | 9 | MPa | ISO 527 |
| Tensile Modulus @ 100% 23°C, 500 mm/min | 6 | MPa | ISO 527 |
| Ultimate Elongation 23°C, 500 mm/min | 320 | % | ISO 527 |
| Tear Strength 23°C, 500 mm/min | 45 | kN/m | ISO 34 (Die C) |

Properties determined on injection molded slabs, 150mm x 100mm x 2mm

Solvay
Engineered Polymers, Inc.
1200 Harmon Road
Auburn Hills, MI 48326
Phone: (248) 391-9500
Fax: (248) 391-9501

NexPrene[®] is a registered trademark of Solvay Engineered Polymers, Inc. To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Engineered Polymers, Inc., nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use in compliance with applicable law, the manner of use, and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes. Solvay Engineered Polymers, Inc., reserves the right to make additions, deletions, or modifications to the information at any time without prior notification.

