



NEXPRENE 9560A BLK

DESCRIPTION:

NexPrene® 9560A BLK UV thermoplastic vulcanizate is a fully weatherable crosslinked, EPDM/PP compound designed to replace thermoset elastomers, such as EPDM or polychloroprene, and traditional thermoplastic TPVs. NexPrene® 9560A BLK UV provides excellent chemical resistance and physical properties. This product has substantially lower viscosity compared to traditional TPVs and TPEs; allowing for thin wall and difficult molding applications. It is fully recyclable and can be processed using conventional thermoplastic equipment.

APPLICATIONS:

Suitable for applications requiring flexibility in the following markets: automotive, appliance, business machines, construction, consumer products, electrical & electronics, fluid delivery, hardware, and medical devices.

PROPERTY	TYPICAL VALUE	UNITS	TEST METHOD
PHYSICAL			
Hardness:			
Injection Molded, 5 sec	63	Shore A	ASTM D-2240
Extrusion, 5 sec	59		
Injection Molded, 15 sec	60		ISO 868
Specific Gravity 23°C	0.94		ASTM D-792 ISO 1183
Compression Set			
22 hr @ 70°C	16	%	ASTM D-395
70 hr @ 125°C	48		ISO 815
			ASTM D-395 ISO 815
Brittle Point	-70	°C	ASTM D-746 ISO 812
Ozone Resistance 500 hr, 100 pphm O ₃ conc.	Good		ASTM D-1149
MECHANICAL			
Tensile Strength 23°C, 500 mm/min	4.5	MPa	ASTM D-412 ISO 527
Tensile Modulus @ 100% 23°C, 500 mm/min	2.6	MPa	ASTM D-412 ISO 527
Ultimate Elongation 23°C, 500 mm/min	420	%	ASTM D-412 ISO 527
Tear Strength 23°C, 500 mm/min	26	kN/m	ASTM D-624 (Die C) ISO 34 (Die C)
AMMS			
Parallel	1.2	%	SEP Test Method (fan gate, 6" w X 4" h X 0.125" thick plaque, 85 °F mold temp.)
Transversal	1.6		

10/25/04

Solvay Engineered Polymers
1200 Harmon Road
Auburn Hills, MI 48326
Phone: (248) 391-9500
Fax: (248) 391-9501

NEXPRENE® is trademark of Solvay Engineered Polymers. To our actual knowledge, the information contained herein is accurate as of the date hereof. However, neither Solvay Engineered Polymers, nor any affiliate of company makes any warranty, express or implied, nor accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk, and does not relate to the use of any product in combination with any other substance or in any process. This is not a license under any patent or other propriety right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use, and whether any patents are infringed. The above information gives typical properties only and is not to be used for specification purposes.