

## Product Data Sheet

### SUMITOMO POLYPROPYLENE COPOLYMER

## **AZ564G**

Block Copolymer, Injection Molding

Applications	For industrial applications such as large crates, washing machine parts, electrical appliances, pails and containers, household appliances, and thin walled articles.
Characteristics	High flow, high impact, high stiffness and high heat stability, with nucleating agent.
Typical Processing Conditions	Extrusion temperature : 190°C - 230°C Mold temperature : 20°C - 70°C

### Typical Properties

Physical		Value	Unit	Method
Melt Flow Rate	2.16kg	39	g/10min	ASTM D1238
Density		0.900	g/cm <sup>3</sup>	ASTM D792-A
Mechanical		Value	Unit	Method
Tensile Strength	at Yield	24	MPa	ASTM D638
	at Break	16	MPa	ASTM D638
Flexural Modulus		1280	MPa	ASTM D790
Izod Impact, Notched	23°C	9	kJ/m <sup>2</sup>	ASTM D256
	-20°C	5	kJ/m <sup>2</sup>	ASTM D256
Rockwell Hardness		86		ASTM D785
Thermal		Value	Unit	Method
Vicat Softening Temperature	10N	149	°C	ASTM D1525
Heat Deflection Temperature	0.45MPa	118	°C	ASTM D648
Other		Value	Unit	Method
Shrinkage	MD / TD	1.4 / 1.6		Sumika
Flamability		HB		UL94

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications, actual test results may vary  
Test pieces preparation condition : as per ASTM D4101



**Manufacturer**

AZ564G is manufactured in Saudi Arabia by Rabigh Refining & Petrochemical Co. (Petro Rabigh). Petro Rabigh is an ISO 9001, ISO 14001, and OHSAS 18001 certified company.

**Food Contact Application**

Unmodified AZ564G complies with the requirements of,

- US FDA Regulation 21 CFR 177.1520 and its amendments

Please contact your nearest SCA representative for more information.

**Restriction of Hazardous Substances**

The substances regulated under EU Directive 2011/65/EC on RoHS in electrical and electronic equipment are not used in the manufacturing process of AZ564G and are therefore not expected to be present.

**Storage and Handling**

AZ564G is supplied in 25kg bags or in bulk containers depending on packaging options available for different markets. It is advisable to store in a well ventilated storage facility, protected from rain, direct exposure to sunlight, temperature, and dust.

Moisture may accumulate inside the packaging if there is a significant fluctuation in ambient temperature and high relative humidity. If this occurs, customer is strongly advised to dry the resin prior to use. Direct exposure to sunlight and excessive ambient temperature may affect the properties, appearance, and odor characteristic of the resin.

Please refer to the Safety Data Sheet (SDS) for information regarding industrial health and safety issues.

**Disposal and the Environment**

SCA prioritizes environmental management in all our operations in responsibility and respect towards the community and the environment.

Unmodified AZ564G is readily recyclable, both for reuse via reprocessing and for energy reclamation through incineration. If disposed in landfills, our products, which are inert materials, do not pose pollution risks since they do not generate gaseous or liquid emissions.

