

May 2013

# 6872

**Product Advantages:** TPV with Excellent Compression Set. Processes like a Thermoplastic and acts like a Rubber

Nominal Physical Properties	Test Method	Unit	6872
Density	ISO 1183	g/cm <sup>3</sup>	0.88
Melt Flow (230°C/10Kg)	ISO 1133	g/10min	40
Compression Set (22 hrs @ 70 °C)	ASTM D395	MPa	30
Tensile Modulus at 100% Elongation (M100)	ISO 37 (500 mm/min, Die C)	MPa	4
Tensile Strength	ISO 37 (500mm/min, Die C)	MPa	14
Tensile Elongation	ISO 37 (500 mm/min, Die C)	%	520
Durometer Hardness	ASTM D2240	Shore A	80
Tear Strength (un-nicked angle)	ISO 34	kN/m	40
Oil Resistance Delta V 100 °C, 22hr	JIS K6258	%	52

### Typical Applications:

- Body Seal / Weather stripping
- Interior or Exterior Trim & Over-mold
- Injection Molded & Extruded Parts

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of this information and of our products are beyond our control, this information should not be used in substitution for customers' tests to ensure that Sumitomo Chemical's guidelines are accurate and that our products are safe, effective, and fully satisfactory for the intended end use. We do not represent, warrant, or otherwise guarantee, expressly or impliedly, the suitability, accuracy, reliability, or completeness of this information or the products, guidelines, materials, or processes described. The user is solely responsible for all determinations regarding any use of the information contained herein or the product itself. The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes.

This document reports accurate and reliable information to the best of our knowledge, but our suggestions and recommendations cannot be guaranteed because the conditions of use are beyond our control. Information presented herein is given without reference to any patent questions which may be encountered in the use thereof. Such questions should be investigated by those using this information. Sumitomo Chemical Co., Ltd. Assumes no responsibility for the use of information presented herein and hereby disclaims all liability in regard to such use.

Sumitomo Chemical **North America**

Sumitomo Chemical **Europe**

Sumitomo Chemical **Asia**

**SUMITOMO  
CHEMICAL**

May 2013

# 6872

### Extrusion Equipment Recommendations

Extruder Type	Twin Screw or Single Screw with Mixing Zone
Single Screw Type	Full Flight General Purpose with L/D Ratio > 20:1 & 3:1 Compression Ratio

### Processing Guidelines

Feed Zone	90 °F – 210 °F
Kneading Zone	360 °F – 395 °F
Die	395 °F – 430 °F

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of this information and of our products are beyond our control, this information should not be used in substitution for customers' tests to ensure that Sumitomo Chemical's guidelines are accurate and that our products are safe, effective, and fully satisfactory for the intended end use. We do not represent, warrant, or otherwise guarantee, expressly or impliedly, the suitability, accuracy, reliability, or completeness of this information or the products, guidelines, materials, or processes described. The user is solely responsible for all determinations regarding any use of the information contained herein or the product itself. The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes.

This document reports accurate and reliable information to the best of our knowledge, but our suggestions and recommendations cannot be guaranteed because the conditions of use are beyond our control. Information presented herein is given without reference to any patent questions which may be encountered in the use thereof. Such questions should be investigated by those using this information. Sumitomo Chemical Co., Ltd. Assumes no responsibility for the use of information presented herein and hereby disclaims all liability in regard to such use.

Sumitomo Chemical **North America**

Sumitomo Chemical **Europe**

Sumitomo Chemical **Asia**

**SUMITOMO  
CHEMICAL**