

March 2012

901

Product Advantages: High Melt Flow. Great Value.

Nominal Physical Properties	Test Method	Unit	901
Density	ISO 1183	g/cm ³	0.90
Melt Flow (230°C/2.16Kg)	ISO 1133	g/10min	8.0
Flexural Modulus	ASTM D790	MPa	170
Tensile Strength	ISO 37 (500mm/min, Die C)	MPa	15.0
Tensile Elongation	ISO 37 (500 mm/min, Die C)	%	620
Durometer Hardness	ASTM D2240	Shore D	41

Typical Applications:

- Knobs
- Interior Trim
- Injection Molded Parts

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of this information and of our products are beyond our control, this information should not be used in substitution for customers' tests to ensure that Sumitomo Chemical's guidelines are accurate and that our products are safe, effective, and fully satisfactory for the intended end use. We do not represent, warrant, or otherwise guarantee, expressly or impliedly, the suitability, accuracy, reliability, or completeness of this information or the products, guidelines, materials, or processes described. The user is solely responsible for all determinations regarding any use of the information contained herein or the product itself. The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes.

This document reports accurate and reliable information to the best of our knowledge, but our suggestions and recommendations cannot be guaranteed because the conditions of use are beyond our control. Information presented herein is given without reference to any patent questions which may be encountered in the use thereof. Such questions should be investigated by those using this information. Sumitomo Chemical Co., Ltd. Assumes no responsibility for the use of information presented herein and hereby disclaims all liability in regard to such use.

**SUMITOMO
CHEMICAL**

901

Tool Design Guidelines

Wall Thickness (WT)	2 – 4 mm
Gate Type	Fan Gate
Gate Thickness (GT)	0.6 – 0.9 x WT
Gate Width (GW)	> 2 x GT
Gate Land (GL)	< 0.75 mm
Runner Type	Round
Sprue “O” Diameter	3.5 x WT
Main-Runner (SR)	2.5 x WT
Secondary-Runner (MR)	1.5 x WT
Draft	3° – 6 ° per side
Inside Radius (IR)	WT / 2
Outside Radius (OR)	WT + IR
Surface Texture	Light Stipple
Surface Coating	Nickel / Teflon
Vent Quantity	1 Every Inch
Vent Depth	0.013 – 0.025 mm
Vent Width	5 mm

Processing Guidelines

Nozzle Temp. (°F)	390 – 470
Front Zone (°F)	390 – 470
Middle Zone (°F)	370 – 450
Rear Zone (°F)	350 – 430
Mold Temp. (°F)	70 – 120
Injection Speed	Fast
Screw RPM	Slow
Injection Pressure (%)	20% more than actual transfer pressure
Back Pressure (psi)	50 – 100
Pack/Hold Pressure	40 – 80% of Injection Pressure

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of this information and of our products are beyond our control, this information should not be used in substitution for customers' tests to ensure that Sumitomo Chemical's guidelines are accurate and that our products are safe, effective, and fully satisfactory for the intended end use. We do not represent, warrant, or otherwise guarantee, expressly or impliedly, the suitability, accuracy, reliability, or completeness of this information or the products, guidelines, materials, or processes described. The user is solely responsible for all determinations regarding any use of the information contained herein or the product itself. The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes.

This document reports accurate and reliable information to the best of our knowledge, but our suggestions and recommendations cannot be guaranteed because the conditions of use are beyond our control. Information presented herein is given without reference to any patent questions which may be encountered in the use thereof. Such questions should be investigated by those using this information. Sumitomo Chemical Co., Ltd. Assumes no responsibility for the use of information presented herein and hereby disclaims all liability in regard to such use.