

STYRON™ A-TECH™ 1210

High Impact Polystyrene Resin

Overview

STYRON A-TECH™ 1210 is a newly developed high impact polystyrene (HIPS) resin based on patented technology, offering a unique combination of processability, stiffness, toughness, low gloss and surface smoothness.

Main Characteristics:

- Low gloss and smooth sheet surface
- Ease of processing
- Excellent thermoforming behaviour
- Good blendability with GPPS

Applications:

- Form Fill Seal (FFS) dairy packaging
- Medical device packaging
- Signage sheet
- Sheet applications requiring matt and smooth surface

Complies with:

- Europe Regulation (EC) 10/2011
- U.S. FDA 21 CFR 177.1640
- Consult the regulations for complete details.

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density			
--	1.04 g/cm ³	1.04 g/cm ³	ASTM D792
73°F (23°C)	1.04 g/cm ³	1.04 g/cm ³	ISO 1183
Apparent (Bulk) Density	0.60 g/cm ³	0.60 g/cm ³	ISO 60
Melt Mass-Flow Rate (MFR)			
200°C/5.0 kg	3.4 g/10 min	3.4 g/10 min	ASTM D1238
200°C/5.0 kg ¹	3.4 g/10 min	3.4 g/10 min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus			
-- ²	254000 psi	1750 MPa	ASTM D638
--	254000 psi	1750 MPa	ISO 527-2/1
Tensile Strength			
Yield ²	2830 psi	19.5 MPa	ASTM D638
Yield	2830 psi	19.5 MPa	ISO 527-2/5
Break ²	3190 psi	22.0 MPa	ASTM D638
Break	3190 psi	22.0 MPa	ISO 527-2/5
Tensile Elongation (Break)	65 %	65 %	ASTM D638 ISO 527-2
Flexural Modulus			
-- ³	283000 psi	1950 MPa	ASTM D790
--	283000 psi	1950 MPa	ISO 178
Flexural Strength			
-- ³	5510 psi	38.0 MPa	ASTM D790
--	5510 psi	38.0 MPa	ISO 178

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact Strength	6.7 ft-lb/in ²	14 kJ/m ²	ISO 180/4A
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Vicat Softening Temperature	208 °F	98.0 °C	ISO 306/A120 ASTM D1525 ⁴

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ Procedure B

² 0.20 in/min (5.0 mm/min)

³ Method I (3 point load), 0.051 in/min (1.3 mm/min)

⁴ Rate B (120°C/h), Loading 1 (10 N)



PRODUCT STEWARDSHIP

Trinseo and its affiliated companies have a fundamental concern for all who make, distribute, and use their products and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products so that appropriate steps may be taken to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Trinseo products – from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

CUSTOMER NOTICE

Customers are responsible for reviewing their manufacturing processes and their applications of Trinseo products from the standpoint of human health and environmental quality to ensure that Trinseo products are not used in ways for which they are not suitable. Trinseo personnel are available to answer questions and to provide reasonable technical support. Trinseo product literature, including safety data sheets, should be consulted prior to the use of Trinseo products. Current safety data sheets are available from Trinseo.

No freedom from infringement of any patent owned by Trinseo or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the customer is responsible for determining whether products and the information in this document are appropriate for the customer’s use and for ensuring that the customer’s workplace and disposal practices are in compliance with applicable legal requirements. Although the information herein is provided in good faith and was believed to be accurate when prepared, Trinseo assumes no obligation or liability for the information in this document.

DISCLAIMER

TRINSEO MAKES NO WARRANTIES, EITHER EXPRESS OR IMPLIED, IN THIS DOCUMENT; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE (INCLUDING MEDICAL APPLICATIONS) ARE EXPRESSLY EXCLUDED. SINCE THE CONDITIONS AND METHODS OF USE OF THE INFORMATION AND PRODUCTS REFERRED TO ARE BEYOND TRINSEO’S KNOWLEDGE AND CONTROL, TRINSEO DISCLAIMS ANY AND ALL LIABILITY FOR LOSSES OR DAMAGES THAT MAY RESULT FROM RELIANCE ON THE INFORMATION OR USE OF THE PRODUCTS DESCRIBED HEREIN. TRINSEO MAKES NO WARRANTIES, EXPRESS OR IMPLIED, THAT THE USE OF ANY TRINSEO PRODUCT WILL BE FREE FROM ANY INFRINGEMENT CLAIMS.

GENERAL NOTICE

Any photographs of end-use applications in this document represent potential end-use applications but do not necessarily represent current commercial applications, nor do they represent an endorsement by Trinseo of the actual products. Further, these photographs are for illustration purposes only and do not reflect either an endorsement or sponsorship of any other manufacturer for a specific potential end-use product or application, or for Trinseo, or for specific products manufactured by Trinseo. If products are described as “experimental” or “developmental”: (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Trinseo to change specifications and/or discontinue production, and (4) although Trinseo may from time to time provide samples of such products, Trinseo is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

Copyright ©Trinseo (2019) All rights reserved.
 ™ Trademark of Trinseo S.A. or its affiliates
 ® Responsible Care is a service mark of the American Chemistry Council

Follow us at:

