

# EMERGE™ PC/ABS 7160ECO

## Advanced Resin

### Overview

EMERGE™ ABS/PC 7160ECO advanced resin containing 30% post consumer recycled (PCR) materials and no chlorine or bromine additives. This resin uses the continuous mass ABS technology that achieves a property balance of impact strength, flowability, and ductility to meet the market needs of various thin-wall applications in information technology equipment (ITE) and consumer electronics without painting or coating.

Applications:

- Packaging for ITE
- Enclosures for electronic parts

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.14 g/cm <sup>3</sup>	1.14 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
230°C/3.8 kg	5.5 g/10 min	5.5 g/10 min	
260°C/5.0 kg	31 g/10 min	31 g/10 min	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus <sup>1</sup>			ASTM D638
0.126 in (3.20 mm), Injection Molded	309000 psi	2130 MPa	
Tensile Strength <sup>1</sup>			ASTM D638
Yield, 0.126 in (3.20 mm), Injection Molded	6670 psi	46.0 MPa	
Break, 0.126 in (3.20 mm), Injection Molded	5510 psi	38.0 MPa	
Tensile Elongation <sup>1</sup>			ASTM D638
Yield, 0.126 in (3.20 mm), Injection Molded	2.5 %	2.5 %	
Flexural Modulus <sup>2</sup>			ASTM D790
0.126 in (3.20 mm), Injection Molded	343000 psi	2370 MPa	
Flexural Strength <sup>2</sup>			ASTM D790
0.126 in (3.20 mm), Injection Molded	10600 psi	73.0 MPa	
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.126 in (3.20 mm), Injection Molded	10 ft-lb/in	550 J/m	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness <sup>3</sup>	106	106	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	203 °F	95.0 °C	
264 psi (1.8 MPa), Unannealed	176 °F	80.0 °C	
CLTE			ASTM D696
Flow : 77 to 167°F (25 to 75°C)	4.8E-5 to 4.9E-5 in/in/°F	8.6E-5 to 8.9E-5 cm/cm/°C	
Transverse : 77 to 167°F (25 to 75°C)	5.6E-5 to 5.9E-5 in/in/°F	1.0E-4 to 1.1E-4 cm/cm/°C	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			UL 94
0.04 in (1.0 mm)	HB	HB	
0.13 in (3.2 mm)	HB	HB	

Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Processing (Melt) Temp	464 to 500 °F	240 to 260 °C
Mold Temperature	140 to 194 °F	60 to 90 °C

### Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

<sup>1</sup> 2.0 in/min (50 mm/min)

<sup>2</sup> 0.051 in/min (1.3 mm/min)

<sup>3</sup> 588.4N/60kgf



**PRODUCT STEWARDSHIP**

Trinseo and its affiliated companies have a fundamental concern for all who make, distribute, and use their products and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products so that appropriate steps may be taken to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Trinseo products – from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

**CUSTOMER NOTICE**

Customers are responsible for reviewing their manufacturing processes and their applications of Trinseo products from the standpoint of human health and environmental quality to ensure that Trinseo products are not used in ways for which they are not suitable. Trinseo personnel are available to answer questions and to provide reasonable technical support. Trinseo product literature, including safety data sheets, should be consulted prior to the use of Trinseo products. Current safety data sheets are available from Trinseo.

No freedom from infringement of any patent owned by Trinseo or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the customer is responsible for determining whether products and the information in this document are appropriate for the customer’s use and for ensuring that the customer’s workplace and disposal practices are in compliance with applicable legal requirements. Although the information herein is provided in good faith and was believed to be accurate when prepared, Trinseo assumes no obligation or liability for the information in this document.

**DISCLAIMER**

TRINSEO MAKES NO WARRANTIES, EITHER EXPRESS OR IMPLIED, IN THIS DOCUMENT; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE (INCLUDING MEDICAL APPLICATIONS) ARE EXPRESSLY EXCLUDED. SINCE THE CONDITIONS AND METHODS OF USE OF THE INFORMATION AND PRODUCTS REFERRED TO ARE BEYOND TRINSEO’S KNOWLEDGE AND CONTROL, TRINSEO DISCLAIMS ANY AND ALL LIABILITY FOR LOSSES OR DAMAGES THAT MAY RESULT FROM RELIANCE ON THE INFORMATION OR USE OF THE PRODUCTS DESCRIBED HEREIN. TRINSEO MAKES NO WARRANTIES, EXPRESS OR IMPLIED, THAT THE USE OF ANY TRINSEO PRODUCT WILL BE FREE FROM ANY INFRINGEMENT CLAIMS.

**GENERAL NOTICE**

Any photographs of end-use applications in this document represent potential end-use applications but do not necessarily represent current commercial applications, nor do they represent an endorsement by Trinseo of the actual products. Further, these photographs are for illustration purposes only and do not reflect either an endorsement or sponsorship of any other manufacturer for a specific potential end-use product or application, or for Trinseo, or for specific products manufactured by Trinseo. If products are described as “experimental” or “developmental”: (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Trinseo to change specifications and/or discontinue production, and (4) although Trinseo may from time to time provide samples of such products, Trinseo is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

---

Copyright ©Trinseo (2019) All rights reserved.  
 ™ Trademark of Trinseo S.A. or its affiliates  
 ® Responsible Care is a service mark of the American Chemistry Council

Follow us at:

