

# EMERGE™ PC/ABS 7590

## Advanced Resin

### Overview

EMERGE™ PC/ABS 7590 advanced resin is an ignition-resistant PC/ABS blend that contains no chlorine or bromine additives. Its superior processing makes it ideal for molding large parts and optimizing cycle time productivity in injection molding operations. It has a UL 94 flammability rating of V-0 at 1.5mm. This resin is suitable for use in a wide variety of applications in the information technology equipment and consumer electronics (ITE/CE) markets.

Main Characteristics:

- UL 94 V-0 at 1.5 mm
- Does not contain chlorine or bromine additives

Applications:

- TV, monitor and PC enclosures
- Adaptors and chargers

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.17 g/cm <sup>3</sup>	1.17 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
230°C/3.8 kg	17 g/10 min	17 g/10 min	
260°C/5.0 kg	75 g/10 min	75 g/10 min	
Molding Shrinkage - Flow	4.0E-3 to 6.0E-3 in/in	0.40 to 0.60 %	ASTM D955
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength			ASTM D638
Yield, 0.126 in (3.20 mm), Injection Molded	9000 psi	62.1 MPa	
Break, 0.126 in (3.20 mm), Injection Molded	6700 psi	46.2 MPa	
Tensile Elongation			ASTM D638
Yield, 0.126 in (3.20 mm), Injection Molded	4.0 %	4.0 %	
Break, 0.126 in (3.20 mm), Injection Molded	50 %	50 %	
Flexural Modulus			ASTM D790
0.126 in (3.20 mm), Injection Molded	410000 psi	2830 MPa	
Flexural Strength			ASTM D790
0.126 in (3.20 mm), Injection Molded	14200 psi	97.9 MPa	
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.126 in (3.20 mm), Injection Molded	12 ft-lb/in	640 J/m	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	201 °F	93.9 °C	
264 psi (1.8 MPa), Unannealed	180 °F	82.2 °C	
Vicat Softening Temperature	227 °F	108 °C	ASTM D1525 <sup>1</sup>
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating <sup>2</sup> (0.06 in (1.5 mm))	V-0	V-0	UL 94
Oxygen Index <sup>2</sup>	29 %	29 %	ASTM D2863

Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	175 to 195 °F	79 to 91 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Processing (Melt) Temp	428 to 482 °F	220 to 250 °C
Mold Temperature	140 to 195 °F	60 to 91 °C

### Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

<sup>1</sup> Rate B (120°C/h), Loading 1 (10 N)

<sup>2</sup> This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.



**PRODUCT STEWARDSHIP**

Trinseo and its affiliated companies have a fundamental concern for all who make, distribute, and use their products and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products so that appropriate steps may be taken to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Trinseo products – from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

**CUSTOMER NOTICE**

Customers are responsible for reviewing their manufacturing processes and their applications of Trinseo products from the standpoint of human health and environmental quality to ensure that Trinseo products are not used in ways for which they are not suitable. Trinseo personnel are available to answer questions and to provide reasonable technical support. Trinseo product literature, including safety data sheets, should be consulted prior to the use of Trinseo products. Current safety data sheets are available from Trinseo.

No freedom from infringement of any patent owned by Trinseo or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the customer is responsible for determining whether products and the information in this document are appropriate for the customer’s use and for ensuring that the customer’s workplace and disposal practices are in compliance with applicable legal requirements. Although the information herein is provided in good faith and was believed to be accurate when prepared, Trinseo assumes no obligation or liability for the information in this document.

**DISCLAIMER**

TRINSEO MAKES NO WARRANTIES, EITHER EXPRESS OR IMPLIED, IN THIS DOCUMENT; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE (INCLUDING MEDICAL APPLICATIONS) ARE EXPRESSLY EXCLUDED. SINCE THE CONDITIONS AND METHODS OF USE OF THE INFORMATION AND PRODUCTS REFERRED TO ARE BEYOND TRINSEO’S KNOWLEDGE AND CONTROL, TRINSEO DISCLAIMS ANY AND ALL LIABILITY FOR LOSSES OR DAMAGES THAT MAY RESULT FROM RELIANCE ON THE INFORMATION OR USE OF THE PRODUCTS DESCRIBED HEREIN. TRINSEO MAKES NO WARRANTIES, EXPRESS OR IMPLIED, THAT THE USE OF ANY TRINSEO PRODUCT WILL BE FREE FROM ANY INFRINGEMENT CLAIMS.

**GENERAL NOTICE**

Any photographs of end-use applications in this document represent potential end-use applications but do not necessarily represent current commercial applications, nor do they represent an endorsement by Trinseo of the actual products. Further, these photographs are for illustration purposes only and do not reflect either an endorsement or sponsorship of any other manufacturer for a specific potential end-use product or application, or for Trinseo, or for specific products manufactured by Trinseo. If products are described as “experimental” or “developmental”: (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Trinseo to change specifications and/or discontinue production, and (4) although Trinseo may from time to time provide samples of such products, Trinseo is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

---

Copyright ©Trinseo (2019) All rights reserved.  
 ™ Trademark of Trinseo S.A. or its affiliates  
 ® Responsible Care is a service mark of the American Chemistry Council

Follow us at:

