

EMERGE™ PC/ABS 7710 SK

Advanced Resin

Overview

EMERGE™ PC/ABS 7710 SK Advanced Resin is an ignition-resistant PC/ABS blend that contains no chlorine or bromine additives. This grade has been tested to ISO 10993 Parts 5 & 10 and is suitable for skin contact applications. It has superior processability for injection molding applications, excellent aesthetics and is available in custom colors.

Main Characteristics:

- Tested under ISO 10993 (Parts 5 & 10)
- RoHS Compliant

Applications:

- Medical equipment housings
- Consumer electronics
- Wearable devices

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density			
--	1.17 g/cm ³	1.17 g/cm ³	ASTM D792
--	1.18 g/cm ³	1.18 g/cm ³	ISO 1183/B
Melt Mass-Flow Rate (MFR)			
230°C/3.8 kg	11 g/10 min	11 g/10 min	ASTM D1238
240°C/5.0 kg	20 g/10 min	20 g/10 min	ASTM D1238
260°C/2.16 kg	13 g/10 min	13 g/10 min	ISO 1133
Molding Shrinkage - Flow	4.0E-3 to 6.0E-3 in/in	0.40 to 0.60 %	ISO 294-4
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus			
--	380000 psi	2620 MPa	ASTM D638
0.157 in (4.00 mm), Injection Molded	371000 psi	2560 MPa	ISO 527-2/1
Tensile Strength			
Yield	8700 psi	60.0 MPa	ASTM D638
Yield, 0.157 in (4.00 mm), Injection Molded	7980 psi	55.0 MPa	ISO 527-2/50
Break	7000 psi	48.3 MPa	ASTM D638
Break, 0.126 in (3.20 mm), Injection Molded	6530 psi	45.0 MPa	ISO 527-2/50
Tensile Elongation			
Yield	3.8 %	3.8 %	ASTM D638
Yield, 0.157 in (4.00 mm), Injection Molded	3.8 %	3.8 %	ISO 527-2/50
Break	65 %	65 %	ASTM D638
Break, 0.157 in (4.00 mm), Injection Molded	43 %	43 %	ISO 527-2/50
Flexural Modulus	390000 psi	2690 MPa	ASTM D790
Flexural Strength (Yield)	14000 psi	96.5 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C), Injection Molded	7.1 ft-lb/in ²	15 kJ/m ²	
73°F (23°C), Injection Molded	19 ft-lb/in ²	40 kJ/m ²	
Notched Izod Impact			
-7°F (-22°C)	8.2 ft-lb/in	440 J/m	ASTM D256
0°F (-18°C)	3.7 ft-lb/in	200 J/m	ASTM D256
73°F (23°C)	9.0 ft-lb/in	480 J/m	ASTM D256
-22°F (-30°C), Injection Molded	6.7 ft-lb/in ²	14 kJ/m ²	ISO 180/A
73°F (23°C), Injection Molded	24 ft-lb/in ²	50 kJ/m ²	ISO 180/A
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness			ASTM D785
R-Scale, 0.126 in (3.20 mm), Injection Molded	120	120	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed	195 °F	90.6 °C	ASTM D648
66 psi (0.45 MPa), Unannealed	190 °F	88.0 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	175 °F	79.4 °C	ASTM D648
264 psi (1.8 MPa), Unannealed	171 °F	77.0 °C	ISO 75-2/A
Vicat Softening Temperature			
--	220 °F	104 °C	ASTM D1525 ¹
--	219 °F	104 °C	ISO 306/A120
--	201 °F	94.0 °C	ISO 306/B50
CLTE			ASTM D696
Flow : -40 to 104°F (-40 to 40°C)	3.8E-5 in/in/°F	6.8E-5 cm/cm/°C	
Transverse : -40 to 104°F (-40 to 40°C)	3.8E-5 in/in/°F	6.8E-5 cm/cm/°C	
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	5.2E+15 ohms	5.2E+15 ohms	IEC 60093
Volume Resistivity	1.0E+18 ohms-cm	1.0E+18 ohms-cm	IEC 60093
Electric Strength			IEC 60243-1
0.0630 in (1.60 mm), in Oil	660 V/mil	26 kV/mm	
0.126 in (3.20 mm), in Oil	460 V/mil	18 kV/mm	
Relative Permittivity			IEC 60250
100 Hz	2.86	2.86	
1 MHz	2.80	2.80	
Dissipation Factor			IEC 60250
100 Hz	4.0E-3	4.0E-3	
1 MHz	7.0E-3	7.0E-3	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating ²			UL 94
0.06 in (1.5 mm)	V-0	V-0	
0.08 in (2.0 mm)	5VB	5VB	
0.10 in (2.5 mm)	5VA	5VA	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 in (1.5 mm) ²	1700 °F	925 °C	
0.08 in (2.0 mm) ²	1700 °F	925 °C	
0.10 in (2.5 mm)	1700 °F	925 °C	
0.12 in (3.0 mm) ²	1740 °F	950 °C	
Oxygen Index	28 %	28 %	ASTM D2863

Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 to 194 °F	80 to 90 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Processing (Melt) Temp	446 to 518 °F	230 to 270 °C
Mold Temperature	140 to 194 °F	60 to 90 °C

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ Rate B (120°C/h), Loading 1 (10 N)

² This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.



PRODUCT STEWARDSHIP

Trinseo and its affiliated companies have a fundamental concern for all who make, distribute, and use their products and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products so that appropriate steps may be taken to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Trinseo products – from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

CUSTOMER NOTICE

Customers are responsible for reviewing their manufacturing processes and their applications of Trinseo products from the standpoint of human health and environmental quality to ensure that Trinseo products are not used in ways for which they are not suitable. Trinseo personnel are available to answer questions and to provide reasonable technical support. Trinseo product literature, including safety data sheets, should be consulted prior to the use of Trinseo products. Current safety data sheets are available from Trinseo.

No freedom from infringement of any patent owned by Trinseo or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the customer is responsible for determining whether products and the information in this document are appropriate for the customer's use and for ensuring that the customer's workplace and disposal practices are in compliance with applicable legal requirements. Although the information herein is provided in good faith and was believed to be accurate when prepared, Trinseo assumes no obligation or liability for the information in this document.

DISCLAIMER

TRINSEO MAKES NO WARRANTIES, EITHER EXPRESS OR IMPLIED, IN THIS DOCUMENT; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE (INCLUDING MEDICAL APPLICATIONS) ARE EXPRESSLY EXCLUDED. SINCE THE CONDITIONS AND METHODS OF USE OF THE INFORMATION AND PRODUCTS REFERRED TO ARE BEYOND TRINSEO'S KNOWLEDGE AND CONTROL, TRINSEO DISCLAIMS ANY AND ALL LIABILITY FOR LOSSES OR DAMAGES THAT MAY RESULT FROM RELIANCE ON THE INFORMATION OR USE OF THE PRODUCTS DESCRIBED HEREIN. TRINSEO MAKES NO WARRANTIES, EXPRESS OR IMPLIED, THAT THE USE OF ANY TRINSEO PRODUCT WILL BE FREE FROM ANY INFRINGEMENT CLAIMS.

GENERAL NOTICE

Any photographs of end-use applications in this document represent potential end-use applications but do not necessarily represent current commercial applications, nor do they represent an endorsement by Trinseo of the actual products. Further, these photographs are for illustration purposes only and do not reflect either an endorsement or sponsorship of any other manufacturer for a specific potential end-use product or application, or for Trinseo, or for specific products manufactured by Trinseo. If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Trinseo to change specifications and/or discontinue production, and (4) although Trinseo may from time to time provide samples of such products, Trinseo is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

Copyright ©Trinseo (2019) All rights reserved.

™ Trademark of Trinseo S.A. or its affiliates

® Responsible Care is a service mark of the American Chemistry Council

Follow us at:

