

PULSE™ 920 MG

PC/ABS Engineering Resin

Overview

An inherently matt medium heat, medium impact PC/ABS resin, PULSE™ 920 MG is designed for interior automotive applications where a matt aesthetic is required. Proprietary low gloss technology allows this unique combination of maximum low gloss aesthetics and physical properties.

Automotive Specifications

- DAIMLER DBL 5404.28
- JLR STJLR.51.353
- JLR STJLR.51.5229
- JLR STJLR.51.5262
- VOLKSWAGEN TL 522 31-A

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.12 g/cm ³	1.12 g/cm ³	ISO 1183/B
Apparent (Bulk) Density	0.65 g/cm ³	0.65 g/cm ³	ISO 60
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	17 g/10 min	17 g/10 min	ISO 1133
Spiral Flow ¹	20.1 in	51.0 cm	
Molding Shrinkage	3.5E-3 to 4.5E-3 in/in	0.35 to 0.45 %	ISO 294-4
VOC Content	9.00 µg/g	9.00 µg/g	VDA 277
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	326000 psi	2250 MPa	ISO 527-2/1
Tensile Stress (Yield)	7250 psi	50.0 MPa	ISO 527-2/50
Tensile Strain (Break)	100 %	100 %	ISO 527-2/50
Flexural Modulus ²	305000 psi	2100 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	3.3 ft-lb/in ²	7.0 kJ/m ²	
73°F (23°C)	10 ft-lb/in ²	22 kJ/m ²	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			ISO 75-2/A
264 psi (1.8 MPa), Unannealed	221 °F	105 °C	
Vicat Softening Temperature	252 °F	122 °C	ISO 306/B50
CLTE - Flow (-22 to 176°F (-30 to 80°C))	4.1E-5 in/in/°F	7.3E-5 cm/cm/°C	ISO 11359-2
Injection	Nominal Value (English)	Nominal Value (SI)	
Drying Temperature	221 °F	105 °C	
Drying Time	4.0 hr	4.0 hr	
Processing (Melt) Temp	500 to 554 °F	260 to 290 °C	
Mold Temperature	158 to 194 °F	70 to 90 °C	

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ Melt Temperature: 500°F (260°C), Injection Pressure: 2.61E+4 psi (1.80E+3 bar)

² 0.079 in/min (2.0 mm/min)



PRODUCT STEWARDSHIP

Trinseo and its affiliated companies have a fundamental concern for all who make, distribute, and use their products and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products so that appropriate steps may be taken to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Trinseo products – from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

CUSTOMER NOTICE

Customers are responsible for reviewing their manufacturing processes and their applications of Trinseo products from the standpoint of human health and environmental quality to ensure that Trinseo products are not used in ways for which they are not suitable. Trinseo personnel are available to answer questions and to provide reasonable technical support. Trinseo product literature, including safety data sheets, should be consulted prior to the use of Trinseo products. Current safety data sheets are available from Trinseo.

No freedom from infringement of any patent owned by Trinseo or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the customer is responsible for determining whether products and the information in this document are appropriate for the customer's use and for ensuring that the customer's workplace and disposal practices are in compliance with applicable legal requirements. Although the information herein is provided in good faith and was believed to be accurate when prepared, Trinseo assumes no obligation or liability for the information in this document.

DISCLAIMER

TRINSEO MAKES NO WARRANTIES, EITHER EXPRESS OR IMPLIED, IN THIS DOCUMENT; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE (INCLUDING MEDICAL APPLICATIONS) ARE EXPRESSLY EXCLUDED. SINCE THE CONDITIONS AND METHODS OF USE OF THE INFORMATION AND PRODUCTS REFERRED TO ARE BEYOND TRINSEO'S KNOWLEDGE AND CONTROL, TRINSEO DISCLAIMS ANY AND ALL LIABILITY FOR LOSSES OR DAMAGES THAT MAY RESULT FROM RELIANCE ON THE INFORMATION OR USE OF THE PRODUCTS DESCRIBED HEREIN. TRINSEO MAKES NO WARRANTIES, EXPRESS OR IMPLIED, THAT THE USE OF ANY TRINSEO PRODUCT WILL BE FREE FROM ANY INFRINGEMENT CLAIMS.

GENERAL NOTICE

Any photographs of end-use applications in this document represent potential end-use applications but do not necessarily represent current commercial applications, nor do they represent an endorsement by Trinseo of the actual products. Further, these photographs are for illustration purposes only and do not reflect either an endorsement or sponsorship of any other manufacturer for a specific potential end-use product or application, or for Trinseo, or for specific products manufactured by Trinseo. If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Trinseo to change specifications and/or discontinue production, and (4) although Trinseo may from time to time provide samples of such products, Trinseo is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

Copyright ©Trinseo (2019) All rights reserved.

™ Trademark of Trinseo S.A. or its affiliates

® Responsible Care is a service mark of the American Chemistry Council

Follow us at:

