

# EMERGE™ PC/PET 9500CR SK Advanced Resin

## Overview

EMERGE™ PC/PET 9500CR SK Advanced Resin is a polycarbonate blend with excellent chemical and ignition resistance properties. This grade has been tested to ISO 10993 Parts 5 & 10 and is suitable for skin contact applications. It is designed for use in medical equipment housings and other applications that are subject to repeated exposure to a variety of cleaners and disinfectants commonly used in hospitals. This grade has good aesthetics and excellent toughness. It has a UL 94 rating of V0 at 2.0 mm.

Main Characteristics:

- Excellent chemical resistance
- Tested under ISO 10993 (Parts 5 & 10)

Applications:

- Medical device housings or enclosures

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.29 g/cm <sup>3</sup>	1.29 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
260°C/5.0 kg	10 g/10 min	10 g/10 min	
265°C/5.0 kg	13 g/10 min	13 g/10 min	
Molding Shrinkage			ASTM D955
Flow	6.0E-3 to 9.5E-3 in/in	0.60 to 0.95 %	
Across Flow	5.0E-3 to 7.0E-3 in/in	0.50 to 0.70 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus <sup>1</sup>			ASTM D638
0.126 in (3.20 mm), Injection Molded	338000 psi	2330 MPa	
Tensile Strength <sup>2</sup>			ASTM D638
Yield, 0.126 in (3.20 mm), Injection Molded	7690 psi	53.0 MPa	
Break, 0.126 in (3.20 mm), Injection Molded	6530 psi	45.0 MPa	
Tensile Elongation <sup>2</sup>			ASTM D638
Yield, 0.126 in (3.20 mm), Injection Molded	4.1 %	4.1 %	
Break, 0.126 in (3.20 mm), Injection Molded	80 %	80 %	
Flexural Modulus <sup>3</sup>			ASTM D790
0.126 in (3.20 mm), Injection Molded	329000 psi	2270 MPa	
Flexural Strength <sup>3</sup>			ASTM D790
0.126 in (3.20 mm), Injection Molded	11900 psi	82.0 MPa	
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.126 in (3.20 mm), Injection Molded	14 ft·lb/in	750 J/m	
Instrumented Dart Impact			ASTM D3763
32°F (0°C), 0.126 in (3.20 mm), Injection Molded, Peak Energy	434 in·lb	49.0 J	
32°F (0°C), 0.126 in (3.20 mm), Injection Molded, Total Energy	549 in·lb	62.0 J	
73°F (23°C), 0.126 in (3.20 mm), Injection Molded, Peak Energy	398 in·lb	45.0 J	
73°F (23°C), 0.126 in (3.20 mm), Injection Molded, Total Energy	531 in·lb	60.0 J	



Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness			ASTM D785
R-Scale, 0.126 in (3.20 mm), Injection Molded	110	110	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	228 °F	109 °C	
264 psi (1.8 MPa), Unannealed	174 °F	79.0 °C	
Vicat Softening Temperature	284 °F	140 °C	ASTM D1525 <sup>4</sup>
CLTE - Flow (-40 to 176°F (-40 to 80°C))	4.1E-5 in/in/°F	7.4E-5 cm/cm/°C	ASTM D696
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	5.2E+15 ohms	5.2E+15 ohms	IEC 60093
Volume Resistivity	1.0E+18 ohms-cm	1.0E+18 ohms-cm	IEC 60093
Electric Strength			IEC 60243-1
0.0630 in (1.60 mm), in Oil	790 V/mil	31 kV/mm	
0.126 in (3.20 mm), in Oil	460 V/mil	18 kV/mm	
Relative Permittivity			IEC 60250
100 Hz	3.28	3.28	
1 MHz	3.12	3.12	
Dissipation Factor			IEC 60250
100 Hz	3.0E-3	3.0E-3	
1 MHz	0.020	0.020	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			UL 94
0.06 in (1.5 mm) <sup>5</sup>	V-1	V-1	
0.08 in (2.0 mm) <sup>5</sup>	V-0	V-0	
0.10 in (2.5 mm) <sup>6</sup>	5VA	5VA	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 in (1.5 mm)	1520 °F	825 °C	
0.08 in (2.0 mm)	1760 °F	960 °C	
0.10 in (2.5 mm)	1760 °F	960 °C	
Injection	Nominal Value (English)	Nominal Value (SI)	
Drying Temperature	250 °F	121 °C	
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr	
Processing (Melt) Temp	480 to 540 °F	249 to 282 °C	
Mold Temperature	110 to 150 °F	43 to 66 °C	

## Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

<sup>1</sup> 0.20 in/min (5.0 mm/min)

<sup>2</sup> 2.0 in/min (50 mm/min)

<sup>3</sup> 0.051 in/min (1.3 mm/min)

<sup>4</sup> Rate B (120°C/h), Loading 1 (10 N)

<sup>5</sup> This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.

<sup>6</sup> This rating not intended to reflect hazards presented by this or any other material under actual fire conditions

## trinseo.com

The principles of Responsible Care® and sustainability influence the production of printed literature for Trinseo S.A. and its affiliated companies. As a contribution towards the protection of our environments, Trinseo's printed literature is produced in small quantities and on paper containing recovered/post-consumer fiber and using 100 percent soy-based ink whenever possible.

### PRODUCT STEWARDSHIP

Trinseo and its affiliated companies have a fundamental concern for all who make, distribute, and use their products and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products so that appropriate steps may be taken to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Trinseo products – from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

### CUSTOMER NOTICE

Customers are responsible for reviewing their manufacturing processes and their applications of Trinseo products from the standpoint of human health and environmental quality to ensure that Trinseo products are not used in ways for which they are not suitable. Trinseo personnel are available to answer questions and to provide reasonable technical support. Trinseo product literature, including safety data sheets, should be consulted prior to the use of Trinseo products. Current safety data sheets are available from Trinseo.

No freedom from infringement of any patent owned by Trinseo or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the customer is responsible for determining whether products and the information in this document are appropriate for the customer's use and for ensuring that the customer's workplace and disposal practices are in compliance with applicable legal requirements. Although the information herein is provided in good faith and was believed to be accurate when prepared, Trinseo assumes no obligation or liability for the information in this document.

### NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS

TRINSEO REQUESTS THAT CUSTOMERS REFER TO TRINSEO'S MEDICAL APPLICATION POLICY [HTTP://WWW.TRINSEO.COM/MEDICAL.HTM](http://www.trinseo.com/MEDICAL.HTM) BEFORE CONSIDERING THE USE OF TRINSEO PRODUCTS IN MEDICAL APPLICATIONS. THE RESTRICTIONS AND DISCLAIMERS SET FORTH IN THAT POLICY ARE INCORPORATED BY REFERENCE

For more information on products, innovations, expertise, and other services available from Trinseo, visit [www.trinseo.com](http://www.trinseo.com), or in the U.S. contact us at +1-855-TRINSEO (+1-855-874-6736).

### DISCLAIMER

TRINSEO MAKES NO WARRANTIES, EITHER EXPRESS OR IMPLIED, IN THIS DOCUMENT; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE (INCLUDING MEDICAL APPLICATIONS) ARE EXPRESSLY EXCLUDED. SINCE THE CONDITIONS AND METHODS OF USE OF THE INFORMATION AND PRODUCTS REFERRED TO ARE BEYOND TRINSEO'S KNOWLEDGE AND CONTROL, TRINSEO DISCLAIMS ANY AND ALL LIABILITY FOR LOSSES OR DAMAGES THAT MAY RESULT FROM RELIANCE ON THE INFORMATION OR USE OF THE PRODUCTS DESCRIBED HEREIN. TRINSEO MAKES NO WARRANTIES, EXPRESS OR IMPLIED, THAT THE USE OF ANY TRINSEO PRODUCT WILL BE FREE FROM ANY INFRINGEMENT CLAIMS.

### GENERAL NOTICE

Any photographs of end-use applications in this document represent potential end-use applications but do not necessarily represent current commercial applications, nor do they represent an endorsement by Trinseo of the actual products. Further, these photographs are for illustration purposes only and do not reflect either an endorsement or sponsorship of any other manufacturer for a specific potential end-use product or application, or for Trinseo, or for specific products manufactured by Trinseo. If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Trinseo to change specifications and/or discontinue production, and (4) although Trinseo may from time to time provide samples of such products, Trinseo is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

For additional information not covered by the content of this document or to ensure you have the latest version of this document available, please refer to our website at [www.trinseo.com/contact](http://www.trinseo.com/contact).

Copyright ©Trinseo (2020) All rights reserved.

™ Trademark of Trinseo S.A. or its affiliates

® Responsible Care is a service mark of the American Chemistry Council

Follow us at:

