



**Plaslube® PEEK CF15 TL15 A**

Techmer Polymer Modifiers - Polyetheretherketone

**Action**



**General Information**

**General**

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Carbon Fiber
Additive	• PTFE Lubricant
Features	• High Flow      • Lubricated
Appearance	• Black      • Colors Available
Processing Method	• Injection Molding

**ASTM & ISO Properties <sup>1</sup>**

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density / Specific Gravity	1.43		ASTM D792
Molding Shrinkage - Flow (0.125 in)	2.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.15	%	ASTM D570
<b>Mechanical</b>			
Tensile Strength (Break)	26000	psi	ASTM D638
Tensile Elongation (Break)	1.5	%	ASTM D638
Flexural Modulus	1.80E+6	psi	ASTM D790
Flexural Strength	38000	psi	ASTM D790
<b>Impact</b>			
Notched Izod Impact (73°F, 0.125 in)	1.6	ft-lb/in	ASTM D256
<b>Hardness</b>			
Rockwell Hardness (R-Scale)	118		ASTM D785
<b>Thermal</b>			
Deflection Temperature Under Load (264 psi, Unannealed)	570	°F	ASTM D648
CLTE - Flow	6.0E-6	in/in/°F	ASTM D696
<b>Electrical</b>			
Volume Resistivity	1.0E+5	ohms·cm	ASTM D257
<b>Flammability</b>			
Flame Rating (0.06 in)	V-0		UL 94

**Processing Information**

	Nominal Value	Unit
<b>Injection</b>		
Drying Temperature	300	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	680 to 730	°F
Middle Temperature	680 to 730	°F
Front Temperature	680 to 730	°F
Processing (Melt) Temp	680 to 720	°F
Mold Temperature	350 to 425	°F
Back Pressure	50.0 to 100	psi
Screw Speed	50 to 100	rpm

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.