

## Description

Polypropylene PPR 12232 is a high melt flow index, high transparency random copolymer. It has an excellent food compatibility thanks to its low odour, making it especially suitable for the production of food packaging and houseware products. Its high fluidity accounts for significant cycle time reduction.

We hereby confirm that we do not use peroxide in the manufacturing of the above-mentioned Product.

## Characteristics

	Method	Unit	Typical Value
<b>Rheological properties</b>			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	80
<b>Mechanical properties</b>			
Flexural modulus	ISO 178	MPa	1150
Izod Impact Strength (notched) at 23°C	ISO 180	kJ/m <sup>2</sup>	5
Hardness Rockwell - R-scale	ISO 2039-2		82
<b>Thermal properties</b>			
Vicat Softening Point	ISO 306	°C	
50N-50°C per hour			67
10N-50°C per hour			130
<b>Other physical properties</b>			
Density	ISO 1183	g/cm <sup>3</sup>	0.902
Bulk Density	ISO 1183	g/cm <sup>3</sup>	0.525

## Handling and storage

Please refer to the safety data sheet (SDS) for handling and storage information. It is advisable to convert the product within one year after delivery provided storage conditions are used as given in the SDS of our product. SDS may be obtained from the website: <http://www.totalrefiningchemicals.com>

An Injection Moulding troubleshooting guide is available upon request.

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within Total Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be incurred for infringement or alleged infringement of patents.

