

## Description

**Polypropylene 4252** is a 1.5 melt flow rate impact copolymer designed for improved toughness and high melt strength. This resin offers outstanding processability in combination with excellent mechanical properties. 4252 was specifically developed for the extruded corrugated sheet market.

**High Purity:** Low catalyst residues in Polypropylene 4252 allow extended processing runs without screen pack pluggage.

**FDA:** 4252 complies with all applicable FDA regulations for food contact applications.

**Applications:** 4252 is recommended for corrugated sheet, profile extrusion, blow molding, thermoforming, and slit film for carpet backing applications.

**Processing:** 4252 processes on conventional extrusion equipment with typical melt temperatures of 400-500°F (204-260°C).

## Characteristics

	Method	Unit	Typical Value
<b>Rheological Properties</b>			
Melt Flow	D-1238	g/10 min	1.5
<b>Mechanical Properties<sup>(1)</sup></b>			
Tensile, Strength at Yield	D-638	psi (MPa)	4,000 (28)
Elongation at Yield	D-638	%	6.5
Flexural Modulus	D-790	psi (MPa)	180,000 (1,250)
Izod Impact @ 23°C Notched	D-256A	ft.-lbs/in. (J/m)	>6(>300)
<b>Thermal Properties<sup>(1)</sup></b>			
Melting Point	TOTAL Method	°F (°C)	320-329 (160-165)
Heat Deflection	D-648	°F (°C)	203 (95)
<b>Other Physical Properties</b>			
Density	D-1505	g/cm <sup>3</sup>	0.905

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

4252 7/2017

Polypropylene

