

Description

Polypropylene 4820WZ is a nucleated impact copolymer with a Melt Flow of 35 g/10min.

4820WZ is characterized by improved stiffness, creep resistance, high impact resistance, excellent antistatic properties and has been formulated to allow faster cycling through early demolding.

4820WZ has been developed specifically for the injection molding of garden furniture, housewares, thin-walled articles, and compounding.

Characteristics

	Method	Unit	Typical Value
Rheological Properties			
Melt Flow	D-1238	g/10 min	35
Mechanical Properties			
Tensile, Strength at Yield	D-638	psi (MPa)	4,000 (27)
Elongation at Yield	D-638	%	6
Flexural Modulus	D-790	psi (MPa)	200,000 (1,380)
Izod Impact (Notched) @ 23°C	D-256	ft.-lbs/in. (J/m)	1.5 (80)
@ -20°C	D-256	ft.-lbs/in. (J/m)	0.7 (37)
Charpy Impact Strength @ 23°C	DIN 53453	kJ/m ²	9.5
@ -20°C	DIN 53453	kJ/m ²	4.5
Thermal Properties⁽¹⁾			
Melting Range	TOTAL Method	°C	160-165
Heat Deflection	D-648	°C	100
Vicat Impact Strength	D-1525	°C	150
Other Physical Properties			
Density	ASTM D-1505	g/cm ³	0.905

4820WZ 3/2015

Polypropylene

