

PP

High Impact & Stiffness Block PP

▶ BI320

● Description

BI320 is a high impact & stiffness PP for injection molding application with excellent impact strength and high stiffness. This grade show high falling weight impact at low temperature and good UV stability. It is suitable for crate box, pallet and applications which need the high impact strength/stiffness balance

● Characteristics

- ▶ Excellent stiffness/impact balance
- ▶ High falling weight impact at low temperature

● Applications

- ▶ Pallet, Machine tool box & Crate box

● Physical Properties

Typical Properties	Method (ASTM)	Unit	BI320
Melt flow index	D1238	g/10min	5
Density	D1505	g/cm ³	0.91
Tensile strength at yield	D638	kg/cm ²	290
Elongation at break	D638	%	400
Flexural modulus	D790	kg/cm ²	13,500
Izod impact strength at 23 °C at -20 °C	D256	kgcm/cm	>40 6
Falling impact strength at 23 °C at -20 °C	Hanwha Total	J	22(Ductile) 21(Ductile)
Heat distortion temp.	D648	°C	115

* Data shown above are representative values for reference purposes only, and not to be construed as specifications.

* Data performed by or on behalf of Hanwha Total



● **Food Contact Application**

- ▶ To apply Hanwha Total BI320 to the food packaging, the verification on the suitability is necessary.
- ▶ In case you might need additional technical or regulatory information, please contact Hanwha Total Polymer Technical Service Team.

● **Contacts**

▶ **Product Information & Technical Services**

103, Dokgot 2-ro, Daesan-eup, Seosan-si, Chungcheongnam-do,
Korea, 31900

TEL : 82-41-660-6190 FAX : 82-41-660-6189

Disclaimer

This document is copyright of Hanwha Total petrochemicals Co., Ltd. Any and all information and the values in this document are typical properties for reference, not to be confused with, or regarded as specification. Customers are responsible for determining whether our products and information are suitable for their particular purpose and for ensuring that Customer's location and handling practices are in compliance with laws and regulations. HANWHA TOTAL assumes no obligation or liability for the information in this document. NO EXPRESS WARRANTIES ARE GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY HANWHA TOTAL. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. HANWHA TOTAL is entitled to alter, change or modify any of the content herein at any time without prior notice, but not under any duty to do so.

