



TotalEnergies

TotalEnergies Petrochemicals & Refining USA, Inc.
Polymers Americas

Lumicene® Polypropylene M8825KZ

Technical Data Sheet
Metallocene Polypropylene – Random Copolymer
Produced in the United States

Description

Clarity – M8825KZ exhibits excellent clarity in molded parts.

Impact – M8825KZ produces molded parts with improved impact in comparison to parts molded from conventional clarified random copolymers.

Antistat – M8825KZ contains an antistat to help protect molded parts from dust accumulation.

FDA – M8825KZ complies with all applicable FDA regulations for food contact applications.

Applications – M8825KZ is recommended for injection molding housewares, caps and closures, packaging and other items requiring a balance of impact, clarity and easy mold release.

Processing – M8825KZ resin processes on conventional injection molding equipment with typical melt temperatures of 390°F-450°F (200°C-232°C).

Characteristics

	Method	Unit	Typical Value
Rheological Properties			
Melt Flow	D-1238	g/10 min	30
Mechanical Properties⁽¹⁾			
Tensile Modulus	D-638	psi (MPa)	180,000 (1,240)
Elongation	D-638	%	12
Flexural Modulus	D-780	psi (MPa)	173,000 (1,195)
Izod Impact @ 73 °F, Notched	D-256A	ft.lb/in (J/m)	0.7 (37)
Haze, 0.04" plaques	D-1003	%	8
Thermal Properties⁽¹⁾⁽²⁾			
Melting Point	DSC	°F (°C)	277 (136)
Heat Deflection @ 66 Psi @ 4.64 kg/cm ²	D-648	°F	192
		°C	89
Other Physical Properties			
Density	D-1505	g/cc	0.9

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.
(2) MP determined with a DSC-2 Differential Scanning Calorimeter. Test procedure available upon request.

Rev: Sept 2021

Polypropylene

TOTALENERGIES PETROCHEMICALS & REFINING USA, INC.
POLYMERS AMERICAS
1201 Louisiana Street
Suite 1800
Houston, TX 77002
www.polymers.totalenergies.com

TECHNICAL CENTER
P.O. Box 1200
Deer Park, Texas 77536
Phone: 281-884-7500

1-800-344-3462



All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TotalEnergies products must be guided by the users own methods for selection of proper formulation. TotalEnergies Petrochemicals & Refining USA Inc. disclaims any responsibility for misuse or misapplication of its products. TotalEnergies MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TotalEnergies' liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.

塑料专家 www.ponci.com.cn/wxb/ +13538586433 +18816996168

