

Description

Polypropylene PPH 10042 is a nucleated antistatic homopolymer with a high Melt Flow Index of 35 g/10 min.

Polypropylene PPH 10042 is characterized by high fluidity for high speed injection of thin wall articles such as dairy pots & tubs, salad trays and caps & closures.

Polypropylene PPH 10042 is nucleated and thus has improved rigidity. This coupled with a highly antistatic nature allows for shorter cycle times and easy demoulding.

Characteristics

	Method	Unit	Typical Value
Rheological properties			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	35
Mechanical properties			
Tensile Strength at Yield	ISO 527-2	MPa	35
Elongation at Yield	ISO 527-2	%	8.5
Tensile modulus	ISO 527-2	MPa	1700
Flexural modulus	ISO 178	MPa	1600
Izod Impact Strength (notched) at 23°C	ISO 180	kJ/m ²	3
Charpy Impact Strength (notched) at 23°C	ISO 179	kJ/m ²	3.5
Hardness Rockwell - R-scale	ISO 2039-2		98
Thermal properties			
Melting Point	ISO 3146	°C	165
Vicat Softening Point	ISO 306	°C	
50N-50°C per hour			90
10N-50°C per hour			153
Heat Deflection Temperature	ISO 752	°C	
1.80 MPa - 120°C per hour			57
0.45 MPa - 120°C per hour			105
Other physical properties			
Density	ISO 1183	g/cm ³	0.905
Bulk Density	ISO 1183	g/cm ³	0.525

