

Description

Polypropylene PPH 7069 is homopolymer with a Melt Flow Index of 12 g/10 min with anti-gas fading stabilisation.

Polypropylene PPH 7069 is characterized by medium fluidity for extrusion of continuous filament (CF) & bulk continuous filament (BCF) fibers and staple fibers for carpets.

Characteristics

| | Method | Unit | Typical Value |
|--|------------|-------------------|---------------|
| Rheological properties | | | |
| Melt Flow Index 230°C/2.16 kg | ISO 1133 | g/10 min | 12 |
| Mechanical properties | | | |
| Tensile Strength at Yield | ISO 527-2 | MPa | 32 |
| Elongation at Yield | ISO 527-2 | % | 10 |
| Tensile modulus | ISO 527-2 | MPa | 1550 |
| Flexural modulus | ISO 178 | MPa | 1450 |
| Izod Impact Strength (notched) at 23°C | ISO 180 | kJ/m ² | 3.5 |
| Charpy Impact Strength (notched) at 23°C | ISO 179 | kJ/m ² | 4.5 |
| Hardness Rockwell - R-scale | ISO 2039-2 | | 95 |
| Thermal properties | | | |
| Melting Point | ISO 3146 | °C | 165 |
| Vicat Softening Point | ISO 306 | °C | |
| 50N-50°C per hour | | | 87 |
| 10N-50°C per hour | | | 152 |
| Heat Deflection Temperature | ISO 752 | °C | |
| 1.80 MPa - 120°C per hour | | | 55 |
| 0.45 MPa - 120°C per hour | | | 100 |
| Other physical properties | | | |
| Density | ISO 1183 | g/cm ³ | 0.905 |
| Bulk Density | ISO 1183 | g/cm ³ | 0.525 |

