

Description

Polypropylene PPH 9069 is homopolymer with a Melt Flow Index of 25 g/10 min.

Polypropylene PPH 9069 is intended for applications in non-wovens. It is also suitable for extrusion of bulk continuous filament (BCF) and continuous filament (CF) fibres. Polypropylene PPH 9069 has a special anti gas-fading formulation to significantly reduce yellowing in fibres.

The high fluidity of polypropylene PPH 9069 also makes it especially suitable for high speed injection moulding of thin walled articles.

Characteristics

	Method	Unit	Typical Value
Rheological properties			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	25
Mechanical properties			
Tensile Strength at Yield	ISO 527-2	MPa	32
Elongation at Yield	ISO 527-2	%	9
Tensile modulus	ISO 527-2	MPa	1600
Flexural modulus	ISO 178	MPa	1500
Izod Impact Strength (notched) at 23°C	ISO 180	kJ/m ²	3
Charpy Impact Strength (notched) at 23°C	ISO 179	kJ/m ²	3.5
Hardness Rockwell - R-scale	ISO 2039-2		95
Thermal properties			
Melting Point	ISO 3146	°C	165
Vicat Softening Point	ISO 306	°C	
50N-50°C per hour			89
10N-50°C per hour			153
Heat Deflection Temperature	ISO 752	°C	
1.80 MPa - 120°C per hour			55
0.45 MPa - 120°C per hour			100
Other physical properties			
Density	ISO 1183	g/cm ³	0.905
Bulk Density	ISO 1183	g/cm ³	0.525

