

## Description

Polypropylene PPR 6290 is a random copolymer polypropylene with a Melt Flow Index of 9 g/min for the cast extrusion of films with excellent heat weldability and optical properties.

Polypropylene PPR 6290 is intended for food, magazine or textile packaging, for lamination films... as well as for stationary supplies.

## Characteristics

	Method	Unit	Typical Value
<b>Rheological properties</b>			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	9
<b>Mechanical properties</b>			
Flexural modulus	ISO 178	MPa	850
<b>Thermal properties</b>			
Melting Point	ISO 3146	°C	140
<b>Other physical properties</b>			
Density	ISO 1183	g/cm <sup>3</sup>	0.902
Bulk Density	ISO 1183	g/cm <sup>3</sup>	0.525

