



**TotalEnergies**

Refining & Chemicals  
Polymers

**Description**

Polypropylene PPR 10232 is a nucleated and antistatic random copolymer polypropylene with a Melt Flow Index of 40 g/10 min for the injection moulding of articles with high transparency and excellent surface appearance.

Polypropylene PPR 10232 has an excellent food compatibility thanks to its low odour, making it especially suitable for the production of food packaging and houseware products.

We hereby confirm that we do not use peroxide in the manufacturing of the above-mentioned Product.

**Characteristics**

	Method	Unit	Typical Value
<b>Rheological properties</b>			
Melt Flow Index 230°C/2.16 kg	ISO 1133	g/10 min	40
<b>Mechanical properties</b>			
Tensile Strength at Yield	ISO 527-2	MPa	28
Elongation at Yield	ISO 527-2	%	10
Tensile modulus	ISO 527-2	MPa	1200
Flexural modulus	ISO 178	MPa	1150
Izod Impact Strength (notched) at 23°C	ISO 180	kJ/m <sup>2</sup>	5
Charpy Impact Strength (notched) at 23°C	ISO 179	kJ/m <sup>2</sup>	6
Hardness Rockwell - R-scale	ISO 2039-2		84
<b>Thermal properties</b>			
Melting Point	ISO 3146	°C	147
Vicat Softening Point	ISO 306	°C	
50N-50°C per hour			67
10N-50°C per hour			130
<b>Other physical properties</b>			
Density	ISO 1183	g/cm <sup>3</sup>	0.902
Bulk Density	ISO 1183	g/cm <sup>3</sup>	0.525

Polypropylene

**Handling and storage**

Please refer to the safety data sheet (SDS) for handling and storage information. It is advisable to convert the product within one year after delivery provided storage conditions are used as given in the SDS of our product. SDS may be obtained from the website: [www.polymers.totalenergies.com](http://www.polymers.totalenergies.com).

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. These are typical values not to be construed as specification limits. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within TotalEnergies Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.

